

MC507U

TECHNICAL DATA BULLETIN

GRADE: MC507U

NEMA: G-7, Type

U.L. LISTED: N

DESCRIPTION: MC507U is a utility grade, glass fabric combined with a silicone resin system. It can be substituted for NEMA G-7, in most heating, appliance insulation and some bearing applications. MC507U has excellent strength and electrical properties. MC507U complies with MIL-I-24768/17 – GSG, with the exception of some specific electrical properties.

TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
PHYSICAL PROPERTIES					
Specific Gravity (ASTM D792)		-			1.88
Rockwell Hardness (ASTM D785)	0.250" Build-up	M Scale	100		
Moisture Absorption (ASTM D570)	Condition A	%	0.19		
Flexural Strength (ASTM D790)	Condition A LW / CW	psi (MPa)	24,300 / 21,700 (167.5) / (149.6)		
Izod Impact Strength (ASTM D256)	Condition A LW / CW	ft-lb/in (J/cm)			
	Condition E-48/50 LW / CW	ft-lb/in (J/cm)			17.00 / 11.50 (9.07) / (6.14)
Bonding Strength (ASTM D229)	Condition A	lb (kg)			750 (340.2)

TECHNICAL DATA BULLETIN

GRADE: MC507U

NEMA: G-7, Type

U.L. LISTED: N

TYPICAL PROPERTIES (continued)

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
THERMAL PROPERTIES					
Temperature Index ¹ (UL Bulletin 746b)	Electrical / Mechanical	°C	170 / 220		
Flammability Vertical (UL Bulletin 94)	Condition A	Class	V-0		
ELECTRICAL PROPERTIES					
Dissipation Factor @ 1 MHz (ASTM D150)	Condition A	-	0.018		
	Condition D-24/23	-	0.045		
Relative Permittivity @ 1 MHz (ASTM D150)	Condition A	-	4.55		
	Condition D-24/23	-	4.67		
Breakdown Voltage (ASTM D149)	Condition A	kVolts	55		
	Condition D-48/50	kVolts	32		
Electric Strength (ASTM D149)	Condition A	Volts/mil (kV/cm)	350 (137.8)		
Arc Resistance (ASTM D495)	Condition A	sec		200	

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.