

KYDEX® 6200

Fire-rated sheet for mass transit

INTRODUCTION

KYDEX® 6200 is a proprietary, high performance thermoplastic sheet designed for use in mass transit vehicles such as subways, vans, buses and trains.

GENERAL INFORMATION

KYDEX® 6200 meets both Federal Transit Administration (FTA) and the Federal Rail Administration (FRA) requirements for smoke emission and flammability as tested under ASTM E-662 and ASTM E-162. It is the ideal thermoplastic to solve your mass transportation equipment needs.

SUGGESTED APPLICATIONS

- Seatbacks
- Bulkhead Components
- Window Reveals
- Ceiling Panels

FEATURES

- Available in over 200 developed colours, various textures and thicknesses from 0.71mm (0.028") and up
- Easy to clean graffiti/spray paint, lipstick, pen, grease and grime with cleaners such as Soft Scrub®, Fantastic®, and citrus-based cleaners such as Cirti Kleen HD® (avoid ammoniated cleaners)
- Resistant to a wide range of concentrated chemicals and solvents, withstands frequent cleaning without staining or fading
- Forms to deep draws with low forces when heated to the upper range of 163 - 200°C (325 - 392°F) and an unusually high resistance to hot tearing
- Can be formed on all standard presses and cut on all standard die-cutting machines

ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products.

Please contact our appLab™ department at 800.682.8758 for resources and Safety Data Sheets or visit our website: www.kydex.com.



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

KYDEX® 6200

Fire-rated sheet for mass transit

| PROPERTY | TEST METHOD | TYPICAL VALUE ¹ | |
|---|----------------|--|--------------------------|
| PHYSICAL | | | |
| Specific Gravity | ASTM D792 | 1.40 | |
| Density | ASTM D792 | 1.30 g/cm ³ | 0.051 lb/in ³ |
| Water Absorption, 24 hr. | ASTM D570 | 0.09% | |
| Rockwell Hardness, R-scale | ASTM D785 | 105 | |
| MECHANICAL | | | |
| Tensile Strength | ASTM D-638 | 41.4 MPa | 6,000 psi |
| Tensile Modulus | ASTM D-638 | 2,592 MPa | 376,000 psii |
| Flexural Strength | ASTM D-790 | 63.4 MPa | 9,200 psi |
| Flexural Modulus | ASTM D-790 | 2,413 MPa | 350,000 psi |
| Compressive Strength, yield | ASTM D-695 | 55.5 MPa | 8,050 psi |
| Compressive Modulus | ASTM D-695 | 2,579 MPa | 374,000 psi |
| Shear Strength | ASTM D-732 | 49 MPa | 7,100 psi |
| Bearing Strength, 4% deflection | ASTM D-953 | 33.5 MPa | 4,860 psi |
| Bearing Strength, max. | ASTM D-953 | 199 MPa | 28,800 psi |
| Notched Izod Impact | ASTM D-256 | 187 J/m | 3.5 ft-lb/in |
| Garnder Drop Dart Impact, GE | ASTM D-5420 | >72.3 J | >640 in-lb _f |
| THERMAL | | | |
| Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) Annealed | ASTM D648 | 77.8°C | 172°F |
| Coefficient of Thermal Expansion | ASTM E831 | 76.4 µm/m/°C | 42.4 µin/in/°F |
| ELECTRICAL | | | |
| Dielectric Strength, oil | ASTM D149 | 19.5 kV/mm | 495 V/mil |
| FLAMMABILITY² | | | |
| Flammability: Independent Laboratory Testing | UL Standard 94 | V-0 | |
| Flammability: Independent Laboratory Testing | FMVSS 302 | Pass | |
| Flammability: Flame Spread Index | ASTM E162 | I _s <35 No Burning Drip | |
| Flammability: Smoke Density | ASTM E662 | D _s (1.5) <100 D _s (4.0) <100 | |
| Flammability: Fire Behavior Classification | DIN 5510-2 | S4, ST2, SR2 | |

¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified.
² All thicknesses and colours
 Not intended for specification purposes.



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Email: info@kydex.com

applab™

Phone: 800.682.8758
 Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.