



Technical Data Sheet

3M™ Neoprene High Performance Rubber & Gasket Adhesive 1300L



[Product Details](#)



[Regulatory Info/SDS](#)

Product Description

3M™ Neoprene High Performance Rubber & Gasket Adhesives 1300 and 1300L are the most versatile of our rubber and gasket adhesives. They may be used to bond metal, wood, most plastics, and neoprene, reclaim, SBR, and butyl rubber. They have high immediate strength and excellent heat resistance. 3M Scotch-Weld Adhesive 1300L is a lower solids, lower viscosity version of 3M Adhesive 1300.

Product Features

- 3M™ Neoprene High Performance Rubber & Gasket Adhesive 1300L meets specification requirements of MMM-A-121.
- Temperature performance range is -30°F (-34°C) to 300°F (149°C).
- Bonding Range: 3M Adhesive 1300 up to 12 minutes; 3M Adhesive 1300L up to 8 minutes.
- Bonds neoprene, SBR, butyl and other types of rubber to various substrates.
- 3M Adhesive 1300L is a lower solids viscosity version of 3M Adhesive 1300, for easier brushing and sprayability.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Attribute Name	Value
Net Weight	6.9 to 7.3 lb/gal
Base	Polychloroprene

Typical Physical Properties

Attribute Name	Temperature	Value
Color		Yellow
Solids Content by Weight		26 to 33 %
Carrier Solvent		Petroleum distillate, methyl ethyl ketone and toluene (These products contain non-photochemically reactive solvent)
Flash Point		-26 °C (-14 °F) ¹
Viscosity	27 °C (80 °F)	250 to 1,000 cP ²

¹ Closed Cup

² Brookfield Viscometer RVF #2 spindle @ 20 rpm

Typical Performance Characteristics

180° Peel Adhesion

Substrate: Canvas to Steel

Dwell Time	Temperature	Value
24 h	22 °C (72 °F)	288 oz/in
72 h	22 °C (72 °F)	768 oz/in
120 h	22 °C (72 °F)	816 oz/in
168 h	22 °C (72 °F)	832 oz/in

Dwell Time	Temperature	Value
2 week	22 °C (72 °F)	480 (This value DOES NOT reflect a loss in strength - but do represent an increase in modulus. Because of the adherends and procedure, bond failure is from the canvas. The actual strength of these adhesives is increasing.) oz/in
3 week	22 °C (72 °F)	320 (This value DOES NOT reflect a loss in strength - but do represent an increase in modulus. Because of the adherends and procedure, bond failure is from the canvas. The actual strength of these adhesives is increasing.) oz/in
3 week	-34 °C (-29 °F)	784 oz/in
3 week	66 °C (150 °F)	520 oz/in
3 week	82 °C (180 °F)	416 oz/in

Overlap Shear Strength

Substrate: Birch to Birch
 Temperature: 22 °C (72 °F)
 Dwell Time: 2 week

Test Condition	Value
-30°F(-34°C)	343 lb/in ² ¹
	549 lb/in ² ¹
150°F(66°C)	195 lb/in ² ¹
180°F(82°C)	136 lb/in ² ¹
200°F(93°C)	85 lb/in ² ¹
225°F(107°C)	85 lb/in ² ¹

¹ 1/8in thick substrates

Handling/Application Information

Directions for Use

1. Surface Preparation

Remove all dust, dirt, oil, grease, wax, loose paint, etc. Wiping with a solvent such as methyl ethyl ketone (MEK)* will aid in preparing the surface for bonding.

2. Application Temperature

For best results, the temperature of the adhesive and surfaces to be bonded should be at least 65°F (18°C). If stored below 30°F (-1°C), allow adhesive to warm to room temperature by placing in a warm room only (do not exceed 120°F [49°C]) followed by thorough agitation.

3. Application

Stir well before using. Brush, flow or spray a thin, uniform coating of adhesive to each surface. A coating of 2.5 gms to 3.5 gms/ft.2 dry weight per surface is recommended. Porous surfaces may require more than one coat. A uniform, glossy film indicates sufficient adhesive.

4. Drying Time

Allow adhesive to dry until no longer wet (maximum dry time about 4 minutes).

5. Bonding Range

Once dry, these adhesives have a short bonding range (up to 8 to 12 minutes).

6. Assembly

Position surfaces carefully before assembly. Bonding is immediate upon contact. Apply sufficient pressure to ensure good contact between coated surfaces. Bonded parts may be handled immediately.

7. Reactivation

Greater immediate strength may be obtained by solvent reactivation. To solvent reactivate, coat both surfaces with adhesive and allow to dry tack free. Lightly wipe one surface with methyl ethyl ketone (MEK)* and complete bonding within 30 seconds.

8. Cleanup

Use a solvent such as 3M™ Solvent No. 2* or methyl ethyl ketone (MEK)* to clean brushes immediately after use. Excess adhesive may be removed from other surfaces with 3M™ Citrus Base Cleaner* or equivalent.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow manufacturer’s precautions and directions for use.

Application Equipment

Note: Appropriate application equipment enhances adhesive performance. We suggest the following application equipment for the user’s evaluation in light of the user’s particular purpose and method of application.

1. Pumping:

5 Gallon Pail Dispensing System:

1. 3M™ Neoprene High Performance Rubber & Gasket Adhesive 1300 – 4:1 double acting ball type check pump, 4 cu. in/cycle 3" air motor. Pail cover required to reduce solvent loss.
2. 3M™ Neoprene High Performance Rubber & Gasket Adhesive 1300L
– Use a pressure pot for material supply.

55 Gallon Pail Dispensing System:

1. 3M Adhesive 1300 – 4:1 double acting ball type check pump, 4 cu. in/cycle 3" air motor, bung style pump.
2. 3M Adhesive 1300L – 2:1 divorced design pump.

Accessories:

1. Hose – Samuel Moore Synflex or equivalent, 500 psi working pressure minimum.

Chemical Resistance Requirements:

1. Packings, glands and hoses in contact with this adhesive must be resistant to ketones and aromatic solvents. Nylon and PTFE lined or coated parts are suggested.
2. Spraying:
3M™ Neoprene High Performance Rubber & Gasket Adhesive 1300L

Spray Gun	Air Cap	Fluid Tip	Atomizing Air Pressure	Approximate Air Requirement*	Fluid Flow**
<i>Air Spray – Hand Held</i>					
Binks 2001, 95	63PH	63BSS (.046")	70 psi	21 CFM	6.5 fl. oz./min.
DeVilbiss JGA, MSA	704	FX (.042")	70 psi	17 CFM	5 fl. oz./min.
<i>Air Spray – Automatic</i>					
Binks 21, 95A, 610	63PH	63BSS (.046")	70 psi	21 CFM	6.5 fl. oz./min.
DeVilbiss AGX	704	FX (.042")	70 psi	17 CFM	5 fl. oz./min.

Note: These adhesives are not recommended for Airless Spraying.

*3 H.P. Compressor for intermittent use. 5 H.P. Compressor for continuous use.

**To Measure Fluid Flow: Pressurize fluid source only; pull trigger; flow material into measuring device for 60 seconds; increase or decrease fluid source pressure to obtain desired fluid flow.

All material hoses should be nylon or PVA lined. Packings and glands in contact with these adhesives should be lined or coated with a non-stick surface.

3. Brushes

Use brushes designed for oil based paint.

Industry Specifications

MMM-A-121

Storage and Shelf Life

Store product at 60-80°F (16-27°C) for maximum storage life. Higher temperatures can reduce normal storage life. Lower temperatures can cause increased viscosity of a temporary nature. Rotate stock on a “first in-first out” basis. When stored at the recommended temperature in the original, unopened container this product has a shelf life of 30 months from date of manufacture.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Automotive Disclaimer

Select Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M
Industrial Adhesives and Tapes Division
3M Center, Building 225-35-06
St. Paul, MN 55144-1000
800-362-3550

3M is a trademark of 3M Company.
©3M 2022 (5/22)