

419E Liquid



Premium Acrylic Conformal Coating

419E is a 1-part, UL 746E certified, acrylic conformal coating. It cures to a durable, flexible and smooth finish. It is easy to apply and can be handled in 15 minutes. It may be removed with appropriate strippers, or soldered through for repair or rework.

419E creates a robust moisture barrier that protects printed circuit boards in humid environments. It provides strong protection against moisture, corrosion, fungus, dirt, dust, thermal shock, short circuits, high-voltage arcing, and static discharge.

Features & Benefits

Certified UL 746E (File# E203094)

Certified IPC-CC-830C

Xylene and toluene free

Fluoresces under UV-A light

Suitable for use with selective coating equipment

Cure Instructions

Allow to dry at room temperature for 24 hours, or after letting sit for 15 minutes, cure the coating in an oven at one of these time/temperature options:

Temperature	65 °C	80 °C	100 °C
Time	30 min	15 min	5 min

Storage and Handling

Store between -5 and 27 °C in a dry area, away from sunlight (see SDS).



Available Packaging

Part #	Packaging	Net Vol.	Net Wt.
419E-1L	Can	945 mL	830 g
419E-4L	Can	3.78 L	3.32 kg
419E-20L	Pail	18.9 L	16.6 kg

419E Liquid



Liquid Properties

Binder System	Acrylic	—
Dry Time to Handle	15 min (1 coat) 25 min (2 coats)	—
Minimum Recoat Time	3 min	—
Recommended Film Thickness	25–75 µm	—
Density	0.9 g/mL	ASTM D1475
Viscosity @ 25 °C	160 cP	Brookfield Engineering labs Inc. IPCTM-65- Method 2.4.24.4
Percent Solids	29%	—
Theoretical Coverage @ Recommended Thickness	93 176 cm ² /L	Calculated
Calculated VOC	625 g/L	—
Shelf Life	5 y	—

Cured Properties

UL	746E	—
IPC-CC-830	C revision	—
Color	Clear	—
Resistivity	3.5 x 10 ¹³ Ω·cm	ASTM D257
Breakdown Voltage	>1 500 V	ASTM D149
Dielectric Strength	1 100 V/mil	
Insulation Resistance	1 x 10 ¹² Ω·cm	IPC-TM-650 2.5.7.1
Moisture Insulation Resistance	1 x 10 ¹² Ω·cm	IPC-TM-650 2.6.3.4
Glass Transition Temperature (T _g)	38 °C	ASTM E1545
Coefficient of Thermal Expansion (CTE)	160 ppm/°C (Prior T _g)	ASTM E831
Service Temperature Range	-65–130 °C	—

419E Liquid



Application Instructions

Read the product SDS before using this product (downloadable at www.mgchemicals.com).

Recommended Preparation

Clean the substrate with MG #824 99.9% Isopropyl Alcohol, so the surface is free of oils, dust, and other residues.

Recommended Thinner

When thinning is required, use MG #4352 Thinner 2.

Brush

This product can be applied by brush for rework or touch-ups. Thinning is not required for most brush applications. Desired coating thickness can be achieved in a single application. Applied coating can be cured immediately.

Manual Spray Guns

Use a standard fluid nozzle gun with a minimum tip diameter of 0.8–1.0 mm. The settings listed below are recommendations; however, performance will vary with different brands:

Inlet	Air Flow	Air Cap
20–40 psi	10–15 SCFM	8–10 psi

1. Dilute 1-part coating to 1-part thinner (MG #4352 Thinner 2). Adjust ratio if required.
2. Stir the coating gently, but thoroughly.
3. Spray a test pattern to ensure good flow quality.
4. Tilt the board at 45° and spray a thin even coat from a distance of 20–25 cm (8–10 in). Use spray-and-release strokes with an even motion to avoid paint buildup in one spot. Start and end each stroke off the surface.
5. Wait 3 min between coats to avoid trapping solvent.
6. Rotate the board 90° and spray again to ensure good coverage.

7. Apply additional coats until desired thickness is achieved (go to step 3).

8. Let dry for 15 min at room temperature before applying heat cure.

Dip Coat

Use a Ford or Zahn cup to monitor the viscosity of the coating, as the solvent will evaporate over time.

1. Hang the PCB on a dipping arm.
2. Slowly lower the PCB into a tank and leave immersed in the coating for 2 min to allow penetration.
3. Slowly withdraw the PCB from the tank at a rate of approximately 6" per minute.
4. Let dry for 3 min before applying additional coats or 15 min before heat cure.

Selective Coating

For higher volume applications, coating can be applied via selective coating equipment. The settings listed below are recommendations and performance will vary with different brands.

Settings	PVA	Nordson Asymtek
Platform	PVA 650	SL 940E
Valve	FCS300-ES	SC 280N
Dilution	1:1 with 4352	4:1 with 4352
Air Pressure	0.5 psi	80 psi
Fluid Pressure	5 psi	25 psi
Dispense Height	10 mm	12.7 mm
Pass Width	5 mm	Not available
Coating Speed	100 mm/s	500 mm/s

Clean-up

Clean spray system and equipment with MEK or acetone, MG #434.

Disclaimer: This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.