

8800



Black Flexible Urethane

8800 is a black, 2-part, flexible polyurethane resin. It has a low mixed viscosity and maintains excellent flexibility at low temperatures. In addition, this flexible urethane adheres strongly to a wide variety of substrates, including metals, composites, glass, ceramics, and many plastics.

It is a cost-effective flexible potting option that provides exceptional physical protection and creates minimum stress on circuit boards and surface-mounted devices. It offers superior moisture resistance and is an ideal choice for harsh environments, especially saltwater exposure and marine applications.

Features & Benefits

2:1 mix ratio

Quick working time

24 hour cure at room temperature

Constant service temperature of -50 to 120 °C

Excellent dielectric properties

Ideal underwater potting compound

Cure Instructions

Allow to cure at room temperature for 24 hours, or cure in an oven at one of these time/temperature options:

Temperature	65 °C	80 °C
-------------	-------	-------

Time	30 min	25 min
------	--------	--------

Moisture contamination can create large bubbles and a lumpy appearance. For consistent curing results, ensure that part A is dry before use and the mixture is kept dry during cure. If moisture contamination of part A is suspected, follow the steps below:

1. Pre-heat part A at 65 °C for 2 hours. Mix the heated resin with the appropriate amount of hardener (do not allow the resin to cool as this may create condensation that wets the resin).
2. Mix the 2 components together and cure in an enclosure that has a constant stream of nitrogen gas flowing through to keep the environment dry.



Available Packaging

Part #	Packaging	Net Vol.	Net Wt.
8800-375ML	2 Bottle kit	375 mL	418 g
8800-2.55L	3 Can kit	2.55 L	2.84 kg
8800-10.8L	3 Can kit	10.8 L	12.0 kg
8800-60L	3 Pail kit	60 L	67.0 kg

Storage and Handling

Store between 16 and 27 °C in a dry area, away from sunlight (see SDS). Minimize the time that the container is kept opened and purge with nitrogen before closing if the material is not used up at once.

8800



Liquid Properties

Chemistry	Polyurethane	—
Density	1.1 g/mL (Mixed) 1.1 g/mL (A) 1.2 g/mL (B)	ASTM D1475
Viscosity @ 25 °C	375 cP (Mixed) 300 cP (A) 640 cP (B)	Brookfield Engineering labs Inc. IPCTM-65- Method 2.4.24.4
Mix Ratio	2:1 (Volume) 7:4 (Weight)	—
Working Time ^a	10 min	—
Shrinkage	2.2%	Calculated
Shelf Life	2 y	—

^aBased on 100 g sample. Varies by volume and geometry.

Cured Properties

Flame Retardancy	No	—
Color	Black	—
Density	1.1 g/mL	Hydrostatic Weighing
Service Temperature Range	-50–120 °C	—
Intermittent Temperature	130 °C	—
Thermal Conductivity @ 25 °C	0.3 W/(m·K)	ASTM E1461
Specific Heat Capacity @ 25 °C	2.7 J/(g·K)	
Thermal Diffusivity @ 25 °C	0.1 mm ² /s	
Glass Transition Temperature (T _g)	11 °C	ASTM E1545
Coefficient of Thermal Expansion (CTE)	86 ppm/°C (Prior T _g) 221 ppm/°C (After T _g)	ASTM E831
Hardness	74 A	ASTM D2240
Tensile Strength	4.5 N/mm ²	ASTM D638

8800



Cured Properties Continued

Lap Shear	4.4 N/mm ² (Stainless Steel) 3.1 N/mm ² (Aluminum) 2.4 N/mm ² (ABS) 2.4 N/mm ² (PC)	ASTM D1002
Resistivity	$8.4 \times 10^{12} \Omega \cdot \text{cm}$	ASTM D257
Breakdown Voltage @ 3.175 mm	46 200 V	ASTM D149
Dielectric Strength @ 3.175 mm	370 V/mil	
Dielectric Constant @ 1MHz	3.4	ASTM D150
Dissipation Factor @ 1 MHz	0.2	
Chemical Absorption	7 % (IPA)	—
Weight Gain, 30 days @ 25 °C	2 % (Sulphuric Acid 3%) 3 % (Acetic Acid) 0.3 % (10% NaOH) 0.5 % (10% NaCl) 0.4 % (Water) 0 % (Transmission Oil) 0 % (Transformer Oil) 6 % (Gasoline)	
Water Absorption ^b @ 1 week @ 2 weeks @ 4 weeks	0.02% (water), 0.08% (10% salt water) 0.2% (water), 0.3% (10% salt water) 0.6% (water), 0.8% (10% salt water)	—

^a Sample size: 12.8 mm width, 12.5 mm thickness, and 4.8 g. Cured 1 hour @ 65 °C.

8800



Application Instructions

Read the product SDS and Application Guide for more detailed instructions before using this product.

Recommended Preparation

Clean the substrate with 824 99.9% Isopropyl Alcohol, so the surface is free of oils, dust, and other residues.

Mixing

1. (Optional) Pre-heat part A to improve surface quality.
2. Scrape settled material free from the bottom and sides of the part A container; stir the contents until homogenous.
3. Measure 2 parts by volume of the pre-stirred part A, and pour into the mixing container. Ensure all contents are transferred by scraping the container.
4. Measure 1 part by volume of the part B, and pour into the mixing container. Ensure all contents are transferred by scraping the container
5. Thoroughly mix parts A and B together.
6. (Optional) Put in a vacuum chamber at 25 inHg.
7. Pour the mixture into a container holding the components to be protected.
8. Blanket both parts with nitrogen if the material is not used up to prevent moisture.
9. Close the part A and B containers tightly between uses.

Mixing >500 g at a time decreases working time and can lead to a flash cure. Limit the size of hand-mixed batches. For large production volumes, contact MG Chemicals Technical Support for assistance.

Disclaimer: This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. MG Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.