

Technical Information

Material

Dissipative Polypropylene Material

Surface Resistivity

10^{11}

Static Decay

<1.0 sec

Triboelectric Charge Generation

Negligible

Polycarbonate Compatibility

3,400 psi @ 73°F

Corrosivity

Negligible

Tensile Strength

2000 to 3000

Elongation

500% to 800%

Burst Impact Strength

20 to 30 cm/kg

Tear Propagation

200g

Modulus of Elasticity

10,000 to 15,000 psi

Coefficient of Friction

0.3 Kinetic, Film to Film

Standards

Meets or Exceeds

ANSI/ESD S20.20

Color

Clear