

## Technical Information

### Material

Dissipative Polypropylene Material

### Surface Resistivity

$10^{11}$

### Static Decay

<1.0 sec

### Triboelectric Charge Generation

Negligible

### Polycarbonate Compatibility

3,400 psi @ 73°F

### Corrosivity

Negligible

### Tensile Strength

2000 to 3000

### Elongation

500% to 800%

## Burst Impact Stength

20 to 30 cm/kg

## Tear Propagation

200g

## Modulus of Elasticity

10,000 to 15,000 psi

## Coefficient of Friction

0.3 Kinetic, Film to Film

## Standards

Meets or Exceeds

ANSI/ESD S20.20

## Color

Clear