




# STATFREE® J DISSIPATIVE FOAM RUBBER



**Black**

### Grounding & Cleaning

If the material is used on top of an already properly grounded surface, [grounding hardware](#) may not be necessary. Where no properly grounded surface is available, [grounding hardware](#) is required to provide a path-to-ground. Rtg compliance verification measurements must be made as outlined in ESD TR53 with a [surface resistance meter](#).

See Tech Bulletin [TB-7000](#) for Reztore® Surface & Mat Cleaner Application Instructions.

### Limited Lifetime Warranty:

Desco warrants for one year that Statfree® matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by [Desco Limited Warranty](#).

### RoHS 3, REACH, and Conflict Minerals Statement

See the Desco Industries RoHS 3, REACH, and Conflict Minerals Statement:

<http://www.descoindustries.com/ROHS.aspx>

See the Desco Limited Warranty:

<http://desco.descoindustries.com/Limited-Warranty.aspx>

See the Desco Disclaimer:

<http://desco.descoindustries.com/Disclaimer.aspx>

Specifications and procedures subject to change without notice.

## Specifications

### Standard Document

ANSI/ESD S20.20

### Electrical Properties

#### Color Dissipative Layer<sup>2</sup>

Rtt Resistance:

1 x 10<sup>6</sup> to < 1 x 10<sup>9</sup> ohms

Rtg Resistance:

1 x 10<sup>6</sup> to < 1 x 10<sup>9</sup> ohms

### Physical Properties

Construction:

Cellular foam rubber<sup>1</sup>

Thickness:

0.125" (3.2mm) ±10%

Surface:<sup>2</sup>

Textured surface

Hardness:

45 Shore "A", per ASTM-D412

Weight:

0.28 lbs. per square foot

Density:

Average - 24 lbs. per cubic foot

Corner Radius:

0.75"

Tensile Strength (Machine Direction)

70 PSI

Tensile Strength (Cross Machine Direction)

45 PSI

Tensile Strength Die "b" (Machine Direction)

20 PSI

Tensile Strength Die "b" (Cross Machine Direction)

15 PSI

<sup>1</sup>Rubber material is vulcanized and may contain sulfur.

<sup>2</sup>Color and texture may vary between lots and mills.

### Tolerances:

Width ± 0.250"

Length ± 0.250" every 1 linear foot of running material.

Thickness ±10%

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to condition for at least 4 hours before cutting to size. Always using care trim with a sharp knife or razor blade.

For product listings, [Click Here](#)



Made in the United States of America

## STATFREE® J DISSIPATIVE SHOCK RESISTANT FOAM RUBBER, 0.125" (3.2MM)

# DESCO

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: [Desco.com](http://Desco.com)  
PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407  
PHONE (781) 821-8370

STATFREE® J  
DRAWING PM-114

DATE:  
March  
2021