



STATSHIELD® STANDARD MOISTURE BARRIER BAG



** Bags are printed (hot stamped or thermal transferred) with an ESD protective symbol and a lot code for traceability. **



NOTE: The complete dry package concept of packaging for electronics requires three elements:

[Statshield® Moisture Barrier Bags](#) - To Protect

[Desiccant](#) - To Absorb Moisture

[Humidity Indicator Card](#) - To Monitor Performance

For detailed instructions see Technical Bulletin [TB-2031](#) - Moisture Barrier Bags Application Instructions.

Specifications:

Standard Document

ANSI/ESD S541 (ANSI/ESD S20.20)
ANSI/ESD S11.4

Electrical Properties

Surface Resistance
(both exterior and interior)
Discharge Shielding
Static Shielding
Charge Generation
Teflon
Quartz

Physical Properties

Film Thickness
Width (Inside Dimensions)
Length (Inside Dimensions)
Opening Offset
Puncture Strength
Heat Seal Strength
(Vetrod bar sealer)
Seal Strength
MVTR
Silicone
Non-corrosive
Marking Adhesion

Heat Sealing Properties

Temperature
Time
Pressure

Typical Values

1×10^4 to $< 1 \times 10^{11}$ ohms
 < 10 nJ
20 volts

-0.09 nC/sq. in.
+0.10 nC/sq. in.

Nominal 3.5mil (.09mm) $\pm 10\%$
Nominal -0" / + 1/4"
Nominal +/- 1/8",
0" to 1/4"
>20 lbs

>11 (lb/in width)
>12 PSI
 ≤ 0.02 g/100sq.in./24hours
Not detected
Pass
Pass

300°F – 400°F, 140°C – 204°C
0.6 – 4.5 seconds
30 – 70 PSI, 206 – 482 KPa

Meets Requirements of:
ESD Protective Packaging
Level 2 except MVTR

Test Procedures/Method

ANSI/ESD STM11.11
ANSI/ESD STM11.31
EIA 541

Modified incline plane
Modified incline plane

MIL-STD-3010, 1003

MIL-STD-3010, 2065

ASTM D1876-93
ASTM D882
ASTM F1249
FTIR
MIL-STD-3010, M3005
IPC-TM-650 2.4.1

ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

1. Low charge generation
2. Dissipative or conductive materials for intimate contact
3. A structure that provides electrostatic discharge shielding."

RoHS, REACH and Conflict Minerals, Statement

See the Desco Industries RoHS, REACH, and Conflict Minerals Statement:

https://desco.descoindustries.com/pdf/Regulatory_Statements_Desco_Statshield_Bags.pdf

See the Desco Limited Warranty:

[Desco.DescoIndustries.com/Limited-Warranty.aspx](https://desco.descoindustries.com/Limited-Warranty.aspx)

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc.
See Bag Selection Chart Click [HERE](#).

Specifications and procedures subject to change without notice.



Made in the
United States of America

Statshield® Standard, Moisture Barrier Bag, 3.5MIL (0.09mm)

DESCO

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: [Desco.com](https://desco.com)
PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021
PHONE (781) 821-8370

**DRAWING
NUMBER**
13806

DATE:
September
2021