

Glyptal Inc.

305 Eastern Avenue
Chelsea, Massachusetts 02150

Telephone (617) 884-6918
Fax (617) 884-8376

PRODUCT DATA SHEET 2600

DESCRIPTION

GLYPTAL 2600 Gloss Black Lacquer was designed for general purpose finishing of industrial products. This alkyd nitrocellulose lacquer has excellent weather durability and very good arc resistance and dielectric strength.

SUGGESTED USES

GLYPTAL 2600 can be used where a fast, air-drying finish is desired. Because of its excellent weather durability, this lacquer may be used on exterior surfaces as well as interior surfaces. Electrical equipment, instruments, and switchboards can be coated with this lacquer as well as furniture, toys, and office equipment.

PRODUCT DETAILS

Color	Black
Gloss	High
Flash Point	< 80 °F
Air Dry: Touch	30 minutes
Hard	4 hours
Recoat	Overnight
Coverage (approximate)	350 ft. ² /gal (1 mil dried film)

APPLICATION

GLYPTAL 2600 may be applied by spray or dip methods. When used to finish metal surfaces, it is preferable that a primer such as Glyptal 7920 be used first.

REDUCTION

For spray or dip application, thin 2600 Black Lacquer with approximately equal volume of G1514 Lacquer Thinner to 20-25 seconds #2 Zahn Cup.

SURFACE PREPARATION

Surfaces to be painted should be dry and free from dirt, wax, grease, rust, and oil. Remove grease and oil by washing surface with mineral spirits. Allow surface to dry thoroughly. When painting over a glossy surface, reduce gloss by using fine sand paper or steel wool.

In as much as Glyptal, Inc. has no control over the use to which others put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material and the compositions described herein should make his or her own tests to determine the materials' suitability for his or her own particular use. Statements concerning possible or suggested uses of the material described herein are not to be construed as constituting a license under any Glyptal patent covering such use or as recommendations for use of such materials in the infringement of any patent.

