

Glyptal Inc.

305 Eastern Avenue
Chelsea, Massachusetts 02150

Telephone (617) 884-6918
Fax (617) 884-8376

PRODUCT DATA SHEET 8001

DESCRIPTION

GLYPTAL 8001 is a red, insulating enamel that can be air-dried or baked. Films of this paint have excellent humidity and salt water resistance as well as dielectric strength. Glyptal 8001 Red offers good heat aging properties and oil resistance. This paint is not suitable for the inside coating of dielectric oil containers.

SUGGESTED USES

Glyptal 8001 is suggested for coating motor stators, field coils, end windings, bus bars, and switch bases. It adheres well to molded phenolics and phenolic varnish films. This paint can also be used as a metal primer where some degree of corrosion resistance is needed.

WET SAMPLE

Color	Iron Oxide Red	
% Wt. Solids	56-59%	
Visc.	80-85 KU	
Flashpoint, cc/pm	< 80 °F	
Dielectric Strength (ASTM D115-55)	1800 V/mil (ave.)	
Arc Resistance on Textolite	30 sec	
Solid Weight	13.76 ± 0.2 lb/gal	
	To Touch	4-6 hours
Air Dry	Hard	Overnight
	Recoat	Overnight
Bake Schedule (225-275 °F)	1-3 hours	
Coverage (1 mil DFT)	650 ft ² /gal	

APPLICATION

Glyptal 8001 Red Enamel is designed for use by spray, dip, or flow coat. For best results apply on clean, dry surfaces at temperatures above 50 °F.

Reduction: Spray- Reduce with 1500 Thinner to a viscosity of 24-28 seconds
(#2 Zahn Cup)
Dip or Flow- Reduce with Aromatic 100 to a viscosity of 30-35 seconds
(#2 Zahn Cup)

SURFACE PREPARATION

Surface to be painted should be dry and free from dirt, wax, grease, rust, and oil. Remove all grease and oil by washing surface with mineral spirits.

HAZARDS

WARNING! FLAMMABLE

Keep away from heat, sparks, and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use adequate ventilation.

KEEP OUT OF THE REACH OF CHILDREN.

In as much as Glyptal, Inc. has no control over the use to which others put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material and the compositions described herein should make his or her own tests to determine the materials' suitability for his or her own particular use. Statements concerning possible or suggested uses of the material described herein are not to be construed as constituting a license under any Glyptal patent covering such use or as recommendations for use of such materials in the infringement of any patent.