




# EV Protect 5008



## Technical Data Sheet



## Flame Retardant Encapsulation Foam

 PATENT PENDING

The next generation of our ultra-lightweight, fire retardant, protective encapsulant is here. Our EV Protect 5008 offers battery designers the ability to integrate high-level structural performance characteristics into their battery system which is ideal for cell to pack applications. This ultra-lightweight material minimizes weight addition to the battery pack and when exposed to a thermal event, significantly reduces, or delays thermal propagation. With a reduced viscosity and improved curing speed, the EV Protect 5008 is especially advantageous for those unique, complex, or intricate battery design architecture. Works in all types of battery cell form factors (cylindrical, prismatic, or pouch).

<b>Technology/Base:</b>	Polyurethane Foam
<b>Type of Product:</b>	Encapsulant
<b>Components:</b>	Two Component
<b>Curing:</b>	Room Temperature Cure
<b>Appearance / Color:</b>	Grey
<b>Consistency:</b>	Low Viscosity Liquid

### General Information

EV Protect 5008 is generally dispensed using a high-speed dynamic mixer head directly into the battery module. The low viscosity liquid is easily able to flow and self-level at the bottom of the enclosure. Once leveled, the material will foam and rise to approximately 5 times volumetric expansion. After rising, the foam will crosslink and cure creating a semi-structural interconnected foam that encapsulates all components within the module. In the event of a thermal event, the foam will absorb, isolate, and insulate the cells to reduce the chances of thermal propagation.



### Features and Benefits



- Reduces Thermal Propagation
- Ultra-Lightweight
- Low Viscosity & Self Leveling
- Great Vibration and Impact Resistance
- Outstanding Insulation Properties
- Faster Cure Speed for Improved Cycle Times
- No outgassing of Hydrogen gas during curing
- Meets UL94 V0
- Up to 5 Times Expansion Rate
- Ease of Processability
- Cost Effective - Low Volume Usage



**Plug into our EV Adhesive Technology**

Download our app to learn more



# EV Protect 5008



## Technical Data

### Typical Uncured Properties

Property	5008-A	5008-B	Blend
Color	Grey	Clear Amber	Grey
Specific gravity D792/D1475	1.19	1.26	1.22
Viscosity at 25°C (cPs)	2000	400	800
Mix ratio by weight	100	86	
Mix ratio by volume	100	81	
Working time at 25°C (sec)			120
Cream time at 25°C (sec)			180-240
Tack Free time at 25°C (min)			< 60

### Cured Properties

Operating Temperature Range (°C)	-60 - 120
Hardness at 24 / 48 hours (Shore A)	70-80 / 75-85
Foam Density – Free Rise (g/cm <sup>3</sup> )	0.16 – 0.21
Foam Density – Free Rise (pcf)	10 - 13
Thermal Conductivity (W/m-K)	0.07

### Electrical Properties

Property	Test Method	Value
Dielectric Strength (kV/mm)	ASTM D149	TBD
Dielectric Constant at 1MHz	ASTM D-0150	TBD
Dissipation factor at 1MHz	ASTM D-0150	TBD
Volume resistivity (ohm-cm)	ASTM D-0257	TBD
Surface resistivity (ohm)	ASTM D-0257	TBD

### Hand Mixing Instructions for Foams

- Per the stated mix ratio, measure out (either by weight or volume) the appropriate portions of Part A and Part B as into a flat sided container.
- The mixing container should be larger than the amount of total material being mixed to allow for vigorous mixing. For example, for 75 grams of total material we suggest a minimum size of 150 ml container for mixing. For larger amounts, adjust container size appropriately.
- Generally, it's recommended to add the higher density part into the flat sided mixing container first and then add the other part gently on top of the first part. This helps limit pre-reaction of the materials to just the interphase. Scrape the side and bottom of the individual parts containers to ensure nearly all the measured materials are added to the mixing container.
- Start timer and immediately mix vigorously for 20-30 seconds with a spatula or flat sided stir stick. Thoroughly scraping the sides and bottom of cup while mixing. Mixed material should be homogeneous and uniform in appearance.
- At end of mixing time, immediately pour mixed material into mold.
- Immediately clean all tools used in preparations that you wish to reuse with solvent.

#### Note:

The values noted in this data sheet are typical properties only and are not intended to be used as material specifications. For assistance in writing a material specification please contact H.B. Fuller for future details.



### General Information

EV Protect 5008-A / 5008-B is a two-component material. Hand mixing may be difficult. It is recommended that an automated dispensing unit be used with dynamic mixer to mix material. Prior to use, stir the individual parts to ensure they are uniform and homogeneous. Mixing the 5008-A prior to use for 5-10 minutes is essential to achieve a consistent foam density and cell structure. Check the container bottom for sediment after mixing to ensure filler is mixed in. If an extended shutdown or break in production has occurred (> 1 hour) re-mix part A side prior to use. Note: Pail or Drum size containers may require longer mixing times. Surface must be clean, dry, and free from grease, oil, wax and other surface contaminates.



### Handling and Clean-Up

For cleanup of EV Protect 5008, Methyl Ethyl Ketone, Acetone, Dibasic Ester, Ethyl Acetate, or Mineral Spirits are recommended. Confirm with equipment supplier for compatibility of recommended solvents in dispensing equipment. Mineral oil can be used to flush uncured materials from lines. To clean uncured material from tabletops, tools or spatulas, additional cleaning solvent options are Isopropanol and Denatured Alcohol.



### Typical Packaging

5 gal Pails  
55 gal Drums  
300 gal Totes



### Storage and Shelf Life

EV Protect 5008 should be stored in a cool, dry place above 15°C (60°F). Purge open containers with dry nitrogen. Shelf life is a minimum of one year in unopened containers when stored at 25°C.



### Safety and Disposal

For safe handling information on this product, consult the Safety Data Sheet (SDS)

H.B. Fuller Company  
2727 Kinney Ave NW,  
Grand Rapids, MI 49534

(616) 453-8271

www.hbfuller.com

© H.B. Fuller Company, 2022

**IMPORTANT:** The information, specifications, procedures, and recommendations provided (information) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is user's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the users intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

Unless otherwise noted, trademarks are property of H.B. Fuller Company or one of its affiliated entities.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fullers liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.