

HumiSeal® 1B73LOC Acrylic Conformal Coating Technical Data Sheet

HumiSeal® 1B73LOC is a low VOC solvent based conformal coating that complies with most North American air quality regulations. HumiSeal® 1B73LOC is a fast drying, single component, acrylic coating intended for printed circuit assemblies. Cured HumiSeal® 1B73LOC fluoresces under UV light for ease of inspection and is easily repaired. HumiSeal® 1B73LOC coating is MIL-I-46058C qualified, IPC-CC-830 and RoHS Directive 2011/65/EU compliant and recognized under UL File Number E105698.

Properties HumiSeal® 1B73LOC

Density, per ASTM D1475	1.23 ± 0.03 g/cm ³
Solids Content, % by weight per Fed-Std-141, Meth. 4044	26 ± 2 %
Viscosity, per Fed-Std-141, Meth. 4287	445 ± 30 centipoise
VOC	92 grams/litre
Drying Time to Handle per Fed-Std-141, Meth. 4061	25 minutes
Recommend Coating Thickness	25 - 75 microns
Recommended Curing Conditions	24 hrs @ RT or 2 hrs @ 76°C
Time Required to Reach Optimum Properties	7 days
Recommended Thinner	HumiSeal® Thinner 701
Recommended Stripper	HumiSeal® Stripper 1080, 1080A
Shelf Life at Room Temperature, DOM	24 months
Thermal Shock, 50 cycles per MIL-I-46058C	-65°C to 125°C
Coefficient of Thermal Expansion - TMA	67 ppm/°C
Glass Transition Temperature - DSC	42°C
Modulus - DMA	11.1 MPa
Flammability, per UL 94	V-0
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Breakdown Voltage, per ASTM D149	6300 volts
Dielectric Constant, at 1MHz and 25°C per ASTM D150-98	2.6
Dissipation Factor, at 1MHz and 25°C per ASTM D150-98	0.01
Insulation Resistance, per MIL-I-46058C	5.5 x 10 ¹⁴ ohms (550TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	7.0 x 10 ¹⁰ ohms (70GΩ)
Fungus Resistance, per ASTM G21	Passes

Application HumiSeal® 1B73LOC

Conformal coatings can be successfully applied to substrates that have been cleaned prior to coating and also to substrates assembled with low residue “no clean” materials. Users should perform adequate testing to confirm compatibility between the conformal coating and their particular assembly materials, process conditions and cleanliness level. Please contact HumiSeal® for additional information.

Dipping

Depending on the complexity, density and configuration of components on the assembly, it may be necessary to reduce the viscosity of HumiSeal® 1B73LOC with HumiSeal® Thinner 701 in order to obtain a uniform film. Once optimum viscosity is determined, a controlled rate of immersion and withdrawal (5-15 cm/min) will further ensure even deposition of the coating and ultimately a uniform film. During the application, evaporation of solvent

HumiSeal® 1B73LOC Technical Data Sheet

causes an increase in viscosity that should be adjusted by adding small amounts of HumiSeal® Thinner 701. Viscosity in the dip tank should be checked regularly, using a simple measuring device such as a Zahn or Ford viscosity cup.

Spraying

HumiSeal® 1B73LOC can be sprayed using conventional spraying equipment. Spraying should be done in an environment with adequate ventilation so that the vapour and mist are carried away from the operator. The addition of HumiSeal® Thinner 701 is necessary to ensure a uniform spray pattern resulting in pinhole-free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used and operator technique.

Brushing

HumiSeal® 1B73LOC may be brushed with a small addition of HumiSeal® Thinner 701. Uniformity of the film depends on component density and operator's technique.

Storage

HumiSeal® 1B73LOC should be stored away from excessive heat or cold, in tightly closed containers. HumiSeal® products may be stored at temperatures of 0 to 35°C. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32°C.

Caution

Application of HumiSeal® Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

The solvents in HumiSeal® Conformal Coatings are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult SDS prior to use.

Contact HumiSeal®

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrières-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.