

EP256HA Solder Paste

No-Clean

Product Description

EP256HA Solder Paste is a no-clean, air or nitrogen reflowable solder paste specifically designed to provide maximum print characteristics and solderability on lead-free parts using leaded solder paste. EP256HA has been designed for applications that require the ultimate activity with respect to difficult to solder to components and board surface metalizations. EP256HA is also capable of stencil printing after downtimes of up to 90 minutes with an effective first print down to 20 mils. EP256HA is a solder paste formula that maintains its activity and printing characteristics for up to 8 hours without any shear thinning.

Performance Characteristics:

- Excellent solderability on difficult to solder to components, i.e., PdAg
- High activity on all substrates, including OSPs
- Capable of 90-minute break times in printing
- Excellent printing characteristics to 0.4 mm (16 mil) pitch with Type 3 powder
- High print speeds to 150 mm/sec (6 in/sec)
- Stable tack over 8+ hours
- Stencil life: 8+ hours (process dependent)
- Scrap is reduced due to less paste dry out
- Classified as ROL0 per J-STD-004

Standard Applications:

For stencil printing: 90% Metal

RoHS Compliance

Kester does not determine any applicable Restriction of Hazardous Substances (RoHS) exemptions for our lead containing products at the user level.

Physical Properties

(Data given for Sn63Pb37, 90% metal, -325+500 mesh)

Viscosity (typical): 1600 poise

Malcom Viscometer @ 10 rpm and 25 °C

Initial Tackiness (typical): 37 grams
Tested to Kester Method 1W-QC-3-04

Slump Test: Pass
Tested to J-STD-005, IPC-TM-650, Method 2.4.35

Solder Ball Test: Pass
Tested to J-STD-005, IPC-TM-650, Method 2.4.43

Wetting Test: Pass
Tested to J-STD-005, IPC-TM-650, Method 2.4.45

Reliability Properties

Copper Mirror Corrosion: Low
Tested to J-STD-004, IPC-TM-650, Method 2.3.32

Corrosion Test: Low
Tested to J-STD-004, IPC-TM-650, Method 2.6.15

Silver Chromate: Pass
Tested to J-STD-004, IPC-TM-650, Method 2.3.33

Chloride and Bromides: None Detected
Tested to J-STD-004, IPC-TM-650, Method 2.3.35

Fluorides by Spot Test: Pass
Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

Surface Insulation Resistivity (SIR): Pass
Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3


Availability

EP256HA is commonly available in the Sn63Pb37 and Sn62Pb36Ag02 alloys. Type 3 powder mesh is recommended, but different powder particle size distributions are available for standard and fine pitch applications. For specific packaging information, see Kester's Solder Paste Chart for available sizes. The appropriate combination depends on process variables and the specific application.

Printing Parameters

Squeegee Blade	80 to 90 durometer polyurethane or stainless steel
Squeegee Speed	Capable to a maximum speed of 200 mm/sec (8 in/sec)
Stencil Material	Stainless Steel, Molybdenum, Nickel Plated, Brass
Temperature/Humidity	Optimal ranges are 21 to 25 °C (70 to 77 °F) and 35 to 65% RH

Recommended Reflow Profile



The recommended reflow profile for EP256HA made with either the Sn63Pb37 or Sn62Pb36Ag02 is shown here. This profile is simply a guideline. Since EP256HA is a highly active solder paste, it can solder effectively over a wide range of profiles. EP256HA is capable of reflowing at the 235 °C peak temperatures required for fully collapsing lead-free SAC BGA's for maximum reliability and remains easy to clean after these high temperature profiles. Your optimal profile may be different from the one shown based on your oven, board and mix of defects. Contact Kester Technical Support if you need additional profiling advice.

Cleaning

EP256HA is a no-clean formula. The residues don't need to be removed for typical applications. Although EP256HA is designed for no-clean applications, its residues can be easily removed using automated cleaning equipment (in-line or batch) with a variety of readily available cleaning agents. Call Kester Technical Support for details.

Storage, Handling and Shelf Life

Refrigeration is the recommended optimum storage condition for solder paste to maintain consistent viscosity, reflow characteristics and overall performance. EP256HA should be stabilized at room temperature prior to printing. EP256HA should be kept at standard refrigeration conditions, 0 to 10 °C (32 to 50 °F). Contact Kester Technical Support if you require additional advice with regard storage and handling of this material. Shelf life is 6 months from the date of manufacture when handled properly when held at 0 to 10 °C (32 to 50 °F).

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at <https://www.kester.com/downloads/sds>.

Contact Information

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

North America 800 West Thorndale Avenue Itasca, IL USA 60143 Phone: +1 800.2.KESTER	Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong Phone: +852.3190.3100	Europe Ganghofer Strasse 45 82216 Gernlinden, Germany Phone: +49 (0) 8142 4785 0
---	--	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.