

5560 Solder-Nu™ Cleaner

For Solder and Silver

Product Description

Kester 5560 Solder Nu Metal Cleaner is a non-fuming liquid solution for removing oxides, sulfides, carbonates and other contamination, such as etch residues, from copper metal surfaces to facilitate soldering. This stable solution cleans by dissolving or solubilizing the contamination for easy removal by water rinsing. The chemical cleaning action is quite different from strong mineral acids which etch away valuable base metal and passivate the surface by insoluble film formation. 5560 contains a pink pH indicator which turns yellow at pH 3.5 indicating the solution has lost its efficiency. 5560 is a non-foaming chemical for use in spray cleaning equipment. Because the etch rate is controlled, the bath life is very extended. 5560 will selectively remove surface contamination from solder-plated or tin-plated surfaces as well as very tarnished copper surfaces. 5560 is very effective in cleaning silver-plated surfaces with no appreciable metallic etching.

Performance Characteristics:

- Removes oxidation to facilitate soldering
- Easily cleaned in water
- Minimal etching

RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive, 2015/863 for the stated banned substances.

Physical Properties

Specific Gravity: 1.085 ± 0.010

Antoine Paar DMA 35 @ 25 °C

pH (10% solution): 1.01

Hanna Instruments 8314 @ 25 °C

Flash Point: >100 °C (212 °F)

Flux Application

Surfaces to be cleaned should be free of oil and grease. 5560 should be used as received in plastic or glass containers at room temperature or hot 49 to 60 °C (120 to 140 °F). Heating the solution accelerates the rate at which 5560 reacts with contaminants. Parts are immersed for 30 seconds to 3 minutes depending on the condition of the surface and then water rinsed to remove the solubilized contamination. Residual water insoluble metallic complexes can be removed from an etched surface with minimal etching of the metal. Plating or etching residues can seriously affect the reliability of a soldered connection.

Cleaning

No neutralizer, saponifiers or detergents are necessary in the water wash system for complete removal of residues. It is not recommended to use high mineral content tap water. Otherwise, tap, deionized or softened water may be used for cleaning.

Storage, Handling and Shelf Life

Because this formulation is water based, it is subject to freezing. A minimum storage temperature of 4 °C (40 °F) is recommended. If frozen, the 5560 is easily reconstituted by stirring at room temperature. Shelf life is 2 years from date of manufacture when handled properly and held at 4 to 25 °C (40 to 77 °F).

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at this [link](#).

Contact Information

To confirm this document is the most recent version, please contact

Assembly@MacDermidAlpha.com

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.253.7837</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
--	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "®" and "™" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.