

## LOCTITE® SF 7109™

June 2023

### PRODUCT DESCRIPTION

LOCTITE® SF 7109™ provides the following product characteristics:

<b>Technology</b>	Activator for Cyanoacrylate
<b>Chemical Type</b>	Amine (active ingredient)
<b>Solvent</b>	Hydrofluoroether
<b>Active Ingredient Concentration, %</b>	0.6 to 0.85
<b>Appearance</b>	Colorless transparent liquid
<b>Viscosity</b>	Very low
<b>Cure</b>	Not applicable
<b>Application</b>	CA adhesive cure accelerator

LOCTITE® SF 7109™ is an activator used where increased cure speed of cyanoacrylate adhesives is required. It can be either pre- or post-applied to the bond. The product is non-flammable.

### TYPICAL PROPERTIES

Specific Gravity @ 23 °C	1.42
Viscosity, 25°C, mPa·s (cP):	0.87
Drying Time @ 23°C, seconds	≤5
On Part Life, minutes	≤1

### TYPICAL PERFORMANCE


#### Effect on Cure Speed of Cyanoacrylate Adhesives

Fixture time and cure speed achieved as a result of using LOCTITE® SF 7109™ depend on the adhesive used and the substrate bonded. The fixture time is defined as the time to develop a shear strength of 0.1 N/mm<sup>2</sup>.

Fixture Time, ISO 4587, seconds:	≤5
Steel (grit blasted) using LOCTITE® 416™, single side activation	

#### Strength vs. Time

The graph below shows the shear strength developed with time using LOCTITE® SF 7109 with LOCTITE® adhesive 416™. Testing was performed @ 22°C in accordance with ISO 4587.



### TYPICAL PERFORMANCE OF CURED MATERIAL

After 2 minutes @ 22°C

Lap Shear Strength, ISO 4587:	N/mm <sup>2</sup>	7.8
Steel (Grit Blasted), with 416™ adhesive	(psi)	(1130)

### GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

**Under no circumstances should activator and adhesive be mixed directly as liquids.**

**Use only in a well-ventilated area.**

#### Direction for use

#### Post Activation

1. Apply LOCTITE® cyanoacrylate to the parts to be bonded or fixed.
2. Apply activator over all exposed cyanoacrylate adhesive by spray or drop. (Typically use one drop of activator per drop of exposed adhesive).

## Surface Activation

1. Apply one coating of Activator to the area to be bonded by spray, brush or dipping. Contaminated surfaces may need special cleaning or degreasing prior to activation to remove any soluble contamination.
2. Allow LOCTITE® SF 7109™ to fully evaporate from parts prior to bonding to avoid solvent entrapment within the bond joint.
3. Apply the LOCTITE® cyanoacrylate product immediately after drying or not more than 45 seconds thereafter.
4. Activator can be re-applied if necessary if there is a delay of more than 45 seconds between original activator and adhesive application.

## Handling Precautions

The solvent can affect certain plastics or coatings. It is recommended to check all surfaces for compatibility before use.

## Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8°C to 21°C. Storage below 8°C or greater than 28°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

## Product Specification

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

## Approval and Certificate

Please contact Henkel representative for related approval or certificate of this product.

## Data Ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

## Conversions

(°C x 1.8) + 32 = °F  
 kV/mm x 25.4 = V/mil  
 mm / 25.4 = inches  
 µm / 25.4 = mil  
 N x 0.225 = lb  
 N/mm x 5.71 = lb/in  
 N/mm² x 145 = psi  
 MPa x 145 = psi  
 N·m x 8.851 = lb·in  
 N·m x 0.738 = lb·ft  
 N·mm x 0.142 = oz·in  
 mPa·s = cP

## Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

## Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office."