

Sn63/Pb37 RA Solder Wires

4880–4888 solder wires use the eutectic tin-to-lead alloy ratio, with a RA-like flux core. They have a low-melting temperature with a sharp melting/solidification point.

They achieve a consistent solder and flux percentage due to our state-of-the-art extrusion wire-drawing machine, which continuously monitors the wire to prevent voids and ensure consistency, providing a top-grade solder wire.



Features & Benefits

- Eutectic alloy (liquidus=solidus temperature)
- Alloy exceeds J-STD-006C, meets J-STD-004B and ASTM B 32 purity requirements
- Rosin-activated flux
- Fast wetting and flowing
- Non-corrosive and non-conductive residue

Available Packaging

Cat. No.	Packaging	Gauge	Diameter	Net Wt.
4880-18G	Pocket pack	21	0.032"	18 g
4884-227G	Spool	23	0.025"	227 g
4884-454G	Spool	23	0.025"	454 g
4885-227G	Spool	21	0.032"	227 g
4885-454G	Spool	21	0.032"	454 g
4886-227G	Spool	19	0.040"	227 g
4886-454G	Spool	19	0.040"	454 g
4887-227G	Spool	18	0.050"	227 g
4887-454G	Spool	18	0.050"	454 g
4888-227G	Spool	16	0.062"	227 g
4888-454G	Spool	16	0.062"	454 g

Contact Information

MG Chemicals, 1210 Corporate Drive
Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com

Phone: North America: +(1)800-340-0772

International: +(1) 905-331-1396

Europe: +(44)1663 362888

Properties

Flux Classification	ROM1 RA
Flux Type	Rosin
Flux Activity	Moderate
Corrosion Test	Pass
Silver Chromate–Cl ⁻ + Br ⁻	Detection
Acid Number (mgKOH/g sample)	150–160
Softening Point of Flux Extract	80 °C
Halides (by weight)	0.5–2.0 %
Surface Insulation Resistance (SIR)	>1.0 x 10 ⁹ Ω

Storage and Handling

Store refrigerated between 18–25 °C away from direct heat or sunlight.

Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.