



SPECIFICATION SHEET

100-95-501

CLEANTEAM® CLEANROOM PAPER

- Paper's antistatic properties reduce attraction of airborne particles and enhance its performance in photocopiers and converting processes
- Inner packs of 250 sheets are ESD (Electrostatic Discharge) sealed
- Chemical and moisture resistant
- Available in white, light blue, yellow, green and pink

APPLICATIONS

- All controlled environments

TECHNICAL DATA

MATERIAL	Synthetic
COLOR	■ Pink, ■ Blue, ■ Green, ■ White, ■ Yellow
SIZE	8.5" x 11"
PACKAGING	250 sheets per inner pack, 10 packs per case
CASE (IN/CM)	12.6 x 17.7 x 4.7 / 32 x 45 x 12
CASE WEIGHT	26.4 lbs / 12 kg
COO	Korea

Basis Weight: 74 g/m² (KSM 7013 test method)

Thickness: 90 micro-m (KSM 7021 test method)

Tensile Strength kg/15mm (MD): 7.7 (KSM 7014 test method)

Tensile Strength kg/15mm (CD): 6.5 (KSM 7014 test method)

Smoothness, sec (top): 29 (KSM 7028 test method)

Smoothness, sec (wire): 26 (KSM test method)

Brightness: 90% (KSM test method)

Opacity: 72% (KSM test method)

Moisture: 6% (KSM test method)

Ash: 0.5% (KSM test method)

Static Build-up (v/cm²):

Before Friction (20° C, 60%RH)	After Friction (20° C, 60%RH)	Surface Resistivity (ohm/sqcm):
5	45	2 x 10 ¹¹

Particle (um):

0.1 - 0.2	0.2 - 0.3	0.3 - 0.5	0.5 - 0.7	0.7 - 1.0	Above 1 um
25	18	30	35	14	59

SEMI G67-0996 test method

Pulp Dissolubility (min): 15 (TAPPI test method)

Extractable ions (ppm):

Na	K	Cl	SO ₄
240*	67*	50**	50**

*SEMI G67-0996 test method

**Leaching method




BARCODES

ITEM	REAM	CASE
■ 100-95-501P	01616314026256	02616314026256
■ 100-95-501B	01616314026232	02616314026232
■ 100-95-501G	01616314026249	02616314026249
■ 100-95-501W	01616314026263	02616314026263
■ 100-95-501Y	01616314026270	02616314026270

DIMENSIONS (in/cm)

	ONE SIZE	---	---
A	11 / 27.9		
B	8.5 / 21.6		



PROTECTIVE INDUSTRIAL PRODUCTS, INC. | BRINGING THE BEST OF THE WORLD TO YOU®

AMERICAS: (800) 262-5755 • (518) 861-0133 | EUROPE: +34-96182-41-48 | AMEA: (ASIA, MIDDLE EAST, AFRICA) 852-2475-9228 | www.pipglobal.com

This document and the information contained herein is the property of Protective Industrial Products, Inc. (PIP) and may not be used or reproduced without permission. Product users should conduct all appropriate testing or other evaluations to determine the suitability of PIP products for a particular purpose or use within a particular environment. PIP DISCLAIMS ALL WARRANTIES OTHER THAN AS EXPRESSLY PROVIDED.