



Main Technical Data:

- **Measuring range:** 0-1000 μ m or 0-40mils
- **Resolution:** 0.1 μ m/0.01mils(0-99 μ m) or 1 m m (over 100 μ m)
- **Guaranteed tolerance:** After one-point calibration: =/- 1-3% n or 2 μ m (whichever is greater)
- **Display:** 4 digits (digit height = 10mm/0.4")
- **Min. measuring area:** 0.2" x 0.2" (5mm x 5mm)
- **Min. radius of curvature:** Convex: 0.12" (3mm) Concave: 1.2" (30mm)
- **Min. substrate thickness:**
Ferrous: 20 mils (0.5mm)
Non-ferrous: 2 mils (50 mm)
- **Calibration:**
Zero Calibration/Foil calibration
* Max. Surface temperature of test object:
302 degrees F
(contact time max is 2 seconds)
- **Power source:** 4-AAA batteries
- **Dimensions:** 161 x 69 x 32mm
- **Weight:** 9oz. (260g)



Coating thickness measurement with Flip Display!

PTG-4200

The PHASE II PTG-4200 can perform two different methods of calculating thickness measurement by utilizing the characteristics of both eddy current and magnetic induction.

Testing performance is both non-destructive and extremely accurate.

With this state of the art thickness gages, you can easily detect the thickness of nonmagnetic coating on a magnetic substrate (ferrous) or an insulating coating on a nonmagnetic conductive substrate (nonferrous) utilizing our auto detect, integrated probe.

The PTG-4200 coating thickness gauge can be used in many areas of industry including automotive auctions, manufacturing, general engineering, commercial inspection, etc.