



Supafil™ Frame US Blowing Insulation

DESCRIPTION

Supafil™ Frame US Blowing Insulation is an unbonded fiberglass blowing insulation designed with optimal thermal properties in addition to excellent coverage and blowing characteristics.

APPLICATION

- Open attics of both new and existing structures
- Loose fill blowing insulation is intended for use where pneumatically installed insulation is most cost-effective

SPECIFICATION COMPLIANCE

- ASTM C764; Type I
- HH-I-1030B; Class B

EQUIPMENT REQUIRED

To achieve labeled R-value, this product must be applied with a pneumatic blowing machine and a corrugated hose with a minimum 0.25" internal corrugation, a minimum length of 150' and a diameter of at least 3". Coils in the hose should not be less than 36" in diameter. The recommended feed rate is 15–25 lbs./min.

FIBERGLASS AND MOLD

Fiberglass insulation will not sustain mold growth. However, mold can grow on almost any material when it becomes wet and contaminated. Carefully inspect any insulation that has been exposed to water. If it shows any sign of mold, it must be discarded. If the material is wet, but shows no evidence of mold, it should be dried rapidly and thoroughly.

CONTRACTOR: _____
 JOB: _____
 DATE: _____

DOING MORE FOR THE WORLD WE LIVE IN.

All of our products are made from sustainable resources, such as recycled glass and sand. And we're proud to be putting glass bottles back to work rather than into landfills. Our products are made with a minimum of 50% recycled glass—totaling an average of 26 million bottles each month.



CERTIFICATIONS



TECHNICAL DATA		
Property (Unit)	Test	Performance
Corrosion	ASTM C764	Pass
Combustibility	ASTM E136	Non-combustible
Water Vapor Sorption (by weight)	ASTM C1104	Less than 5%
Critical Radiant Flux	ASTM E970	Greater than 0.12 W/cm ²
Mold Growth	ASTM C1338	Pass
Surface Burning Characteristics (flame spread/smoke developed)	ASTM E84, CAN 4-S102.2	25/50

Thermal Performance

Supafil™ Frame US provides you with a choice of R-values based on the installed thickness and installed weight per square foot. The tables below show the minimum requirements for obtaining the desired R-value.

The stated thermal resistance (R-value) is provided by installing the required number of bags per 1,000 square feet of net

area, at not less than the labeled minimum thickness (per the manufacturer’s instructions). Failure to install both the required number of bags and at least the minimum thickness will result in lower insulation R-values. Field blending of this product with other loose fill insulation or application of this product in conjunction with adhesive or binder systems may affect its thermal performance and is not recommended by the manufacturer.

OPEN ATTIC COVERAGE					
R-Value*	Bags/1,000 Sq. Ft.	Max. Coverage	Min. Weight	Initial Installed Thickness	Min. Settled Thickness**
To obtain a thermal resistance of:	Number of bags per 1,000 square feet of net area should not be less than:	Contents of this bag should not cover more than:	Weight per square foot of installed insulation should not be less than:	Installed insulation should not be less than:	Installed insulation should not be less than:
R-60	33.2	30.1 sq. ft.	1.136 lbs.	19.500"	19.500"
6-49	26.2	38.0 sq. ft.	0.899 lbs.	16.250"	16.250"
R-44	23.3	43.0 sq. ft.	0.796 lbs.	14.750"	14.750"
R-38	19.7	50.8 sq. ft.	0.673 lbs.	12.875"	12.875"
R-30	15.2	65.9 sq. ft.	0.519 lbs.	10.375"	10.375"
R-26	12.8	77.9 sq. ft.	0.439 lbs.	9.000"	9.000"
R-22	10.8	92.6 sq. ft.	0.369 lbs.	7.750"	7.750"
R-19	9.2	108.4 sq. ft.	0.315 lbs.	6.750"	6.750"
R-13	6.1	165.0 sq. ft.	0.207 lbs.	4.625"	4.625"
R-11	5.2	193.2 sq. ft.	0.177 lbs.	4.000"	4.000"

Bag Net Weight - Nominal 34.1 lbs., Minimum 33.1 lbs.

Coverage and installation data were determined using a Volu-Matic® III blowing machine in third gear with 13" gate opening, 2.5–3.0 PSI air pressure, 150' of 3" diameter internally-corrugated hose. Volu-Matic III is a registered trademark of CertainTeed Corporation.

*"R" means resistance to heat flow. The higher the R-value, the greater the insulating power. To get the marked R-value, it is essential that this insulation be installed properly. If you do it yourself, get instructions and follow them carefully. Instructions do not come with this package.

**Based on Third Party 10-year settling study, the predicted settlement over a 20-year period would be 1 percent or less. This amount of settling is thermally insignificant. Therefore, the installed and settled thicknesses are effectively the same.

Use in the US

In an effort to assist with constrained capacity in the US, Knauf has leveraged the capacity of its global affiliates by importing Supafil Frame US Blowing Insulation from its affiliated manufacturing facilities in Belgium and the Czech Republic. The packaging will specify either "Made in Belgium" or "Made in Czech Republic." Rest assured, the product meets all of the requirements for use in the US and delivers the high-quality performance that is expected from all of Knauf's products. Although the bag dimensions remain the same, the bags do have a new look to better differentiate from our other products. The product has been field-evaluated in Baltimore, Charlotte, and Orlando with exceptional results.

Check with your Knauf Insulation Territory Manager to ensure information is current.

The chemical and physical properties of this product represent average values determined in accordance with accepted test methods. The data is subject to normal manufacturing variations. The data is supplied as a technical service and is subject to change without notice. References to numerical flame spread ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

This product is covered by one or more U.S. and/or other patents.

See patent www.knaufnorthamerica.com/patents

Visit knaufnorthamerica.com to learn more.

KNAUF INSULATION, INC.

One Knauf Drive
Shelbyville, IN 46176

Technical Support

(317) 398-4434 opt. 6

info.us@knaufinsulation.com

05-24

© 2024 Knauf Insulation, Inc.