

Manson Alley-K[®] Pipe Insulation ASJ/SSL with ECOSE[®] Technology - is Listed and Labeled as Plenum Insulation Rated Over Plastic Pipe Assemblies

This Bulletin and the attached Underwriters Laboratories Test Report 4791573466, verifies that Manson Alley-K[®] Pipe Insulation ASJ/SSL with ECOSE[®] Technology is Plenum Rated, and is Listed and Labeled Pipe Insulation by Underwriters Laboratories (UL) File R8583, Category: INSULATED PLASTIC PIPE ASSEMBLIES (BSMP) for installation over polymer pipes (i.e. PVC, CPVC, and polypropylene).

UL Test Report 4791573466 addresses the reference of the 2012, 2015, 2018, 2021 and 2024 International Building Code:

- Section 720.7 Insulation and coverings on pipe and tubing.
 - Exception: Insulation and coverings on pipe and tubing installed in plenums shall comply with the International Mechanical Code.

Per 2012, 2015, 2018 and 2021 International Mechanical Code:

- Section 602.2.1 Materials within plenums. Materials within the plenums shall be noncombustible or shall be listed and labeled with flame spread index not more than 25 and smoke developed index not more than 50 when tested per ASTM E84 or UL 723.
 - Exception #5: Combustible materials fully enclosed within one of the following:
 - 5.3 Material listed and labeled for installation within a plenum and listed for the application.


Per 2024 International Mechanical Code:

- Section 602.3 Materials within plenums. Materials within plenums shall be noncombustible or shall be in compliance with the applicable requirements in Sections 602.3.1 through 602.3.10.
 - Exception # 2. Combustible materials fully enclosed within one of the following:
 - 2.3. Materials listed and labeled for installation within a plenum and listed for the application.

Manson Alley-K[®] Pipe Insulation ASJ/SSL with ECOSE[®] Technology complies with the Fire Hazard Classification (FHC) Flame Spread Index 25/Smoke Developed Index 50 as tested over ¼" thick PVC, CPVC and polypropylene.

For Listing, go to UL Online Certifications Directory; in File Number type: R8583

Certifications



Manson Insulation | www.imanson.com

One Knauf Drive, Shelbyville, IN 46176

Sales 1-800-626-7661

Technical Support (317) 398-4434, option 6

Manufactured by Knauf Insulation

11-25

The trademarks MANSON INSULATION, the design elements and colors, and related marks are trademarks of Knauf Insulation, Inc. or its affiliates.

The Asthma & Allergy Friendly[®] Certification Mark is a Registered Certification Mark of the Asthma Allergy Foundation of America (AAFA) and Allergy Standards Ltd (ASL). Verified Healthier Air[™] is a trademark of Airmid Healthgroup. USGBC[®] and the related logo are trademarks owned by the U.S. Green Building Council[®] and are used with permission.

File Number: R8583

Project Number: 4791573466

Issued: September 25, 2025

Revised: October 7, 2025

REPORT

on

* Knauf Pipe Insulation with **Kraft-Scrim-Foil** Jacket and SSL Closure
Insulated Plastic Pipe Assemblies (BSMP)

Under the

CLASSIFICATION PROGRAM

Knauf Insulation, Inc
Shelbyville, IN

Copyright © 2025 UL LLC

UL LLC authorizes the above named company to reproduce this Report only for purposes as described in the Conclusion, provided it is reproduced in its entirety.

DESCRIPTION

PRODUCT COVERED:

* The Product covered by this Report is a hollow-cylindrical glass-fiber pipe insulation with 30J (**kraft-scrim-foil**) facing on one surface (kraft surface exposed) intended for use in Insulated Plastic Pipe Assemblies.

The product is Classified by UL LLC (UL) as to Surface Burning Characteristics only.

USE

The product is permitted to be installed in ducts, plenums, and other spaces as permitted by authorities having jurisdiction. The pipe assembly is intended for use with PVC, Polypropylene, and CPVC pipes.

TEST RECORD NO. 1
PROJECT 4791573466

GENERAL:

Test results relate only to the items tested.

EXAMINATION OF MATERIALS

The materials used in this investigation were produced under the observation of a representative of UL, in a ready-to-use form. The composition of the finished material is of proprietary nature. Data on the composition is on file at UL for use in the Follow-Up Service Program.

Various physical and chemical tests were conducted on the components and finished products. The results developed from these tests were employed in establishing specifications for use in the factory Follow-Up Service Program.

SURFACE BURNING CHARACTERISTICS:

SAMPLES

* The test samples consisted of Knauf Insulation, Inc glass fiber pipe and equipment covering with **ASJ (30J, kraft-scrim-foil)** facing adhered to the glass fiber. A SSL Closure System was used along the longitudinal seam and a 1/4-inch polypropylene plastic sheet was laid on top of the faced pipe assembly. The kraft side of the facer was exposed to the flame.

Each test sample was supported with 1/4 in. diameter uncoated steel rods and placed at 2 ft intervals.

For each test a piece of 1 ft long by 22 in. wide by 1/16 in. thick uncoated steel plate was placed at the fire end of the tunnel furnace "upstream" from the gas burners to complete the 25 ft chamber length.

The test samples were allowed to condition at a temperature of 73 ±4°F and a relative humidity of 50±5 percent prior to testing.

METHOD

The tests were conducted in accordance with Standard ANSI/UL723, "Test for Surface Burning Characteristics of Building Materials".

RESULTS

Data on flame spread and smoke developed appears in the following tabulations. Graphs of flame spread versus time and smoke developed versus time are also provided as part of the Test Record.

Flame Spread Index

The maximum distance the flame spreads along the length of the sample from the end of the igniting flame is determined by observation.

The Flame Spread Index (FSI) of the material is determined by rounding the Calculated Flame Spread (CFS) as described in UL 723. The CFS is derived by calculating the area under the flame spread distance (ft) versus time (min) curve, ignoring any flame front recession, and using one of the calculation methods as described below.

1. If the total area (A_T) is less than or equal to 97.5 min-ft, the CFS shall be 0.515 times the total area ($FSI=0.515 A_T$).
2. If the total area (A_T) is greater than 97.5 min-ft, the CFS is to be 4900 divided by 195 minus the total area ($FSI=4900/(195-A_T)$).

Table 1: Flame Spread Summary

Test No.	Sample Description	Maximum Flame Spread (ft)	Time of Maximum Flame Spread (min:s)	Calculated Flame Spread (CFS)
*1	ASJ faced glass-fiber pipe insulation (kraft exposed) with ¼-inch Polypropylene sheet backing	3.5	0:15	17.67
*2	ASJ faced glass-fiber pipe insulation (kraft exposed) with ¼-inch Polypropylene sheet backing	4.0	0:16	20.30
*3	ASJ faced glass-fiber pipe insulation (kraft exposed) with ¼-inch Polypropylene sheet backing	4.0	0:16	20.19

Flame Spread Index	20
--------------------	----

Smoke Developed Index

The smoke Developed Index is determined by rounding the Calculated Smoke Developed (CSD) as described in UL 723. The CSD is determined by the output of a photoelectric circuit operating across the furnace flue pipe. A curve is developed by plotting values of light absorption (decrease in cell output) against time. The CSD is derived by expressing the net area under the curve for this material as a percentage of the net area under the curve for untreated heptane.

The CSD is expressed as:

$$CSD = (A_M / A_h) \times 100$$

Where:

CSD=Calculated Smoke Developed

A_M= The area under the curve for the test material

A_h= The area under the curve for untreated heptane

Table 2: Smoke Developed Summary

Test No.	Sample Description	CSD Calculated Smoke Developed
*1	ASJ faced glass-fiber pipe insulation (kraft exposed) with ¼-inch Polypropylene sheet backing	7.2
*2	ASJ faced glass-fiber pipe insulation (kraft exposed) with ¼-inch Polypropylene sheet backing	8.7
*3	ASJ faced glass-fiber pipe insulation (kraft exposed) with ¼-inch Polypropylene sheet backing	7.7

Smoke Developed Index	10
-----------------------	----

Test Record Summary:

The results of this investigation, including construction review and testing, indicate that the products evaluated comply with the applicable requirements in the Standard for Surface Burning Characteristics for Building Materials, UL723, Eleventh Edition (dated June 23, 2025) and, therefore, such products are judged eligible to bear UL's Mark as described below and on the Conclusion Page of this Report.

Any information and documentation provided to you involving UL Mark services are provided on behalf of UL or any authorized licensee of UL.

Classification Marking:

The surface Burning Characteristics as shown below in the Classification Marking represent the judgment of UL based upon the results of the examination and tests presented in this Report.



Insulated Plastic Pipe
Assemblies - Pipe Covering

CERTIFIED IN ACCORDANCE WITH IMC, SECTION 602.1, EXCEPTION 5.3.

* DURING INSTALLATION, A MINIMUM 1-INCH THICK **KRAFT-SCRIM-FOIL** FACED PIPE COVERING IS REQUIRED TO COVER PVC, POLYPROPYLENE, AND CPVC PIPES WITH A MAXIMUM 1/4-INCH WALL THICKNESS

Test Record by:

Brian Foley

Brian Foley
Engineer
Built Environment

Reviewed by:

Jamila Shawon

Jamila Shawon
Staff Engineer
Built Environment

Courtney Hudson

Courtney Hudson
Senior Project Engineer
Built Environment

Conclusion

Samples of the product covered by this Report have been found to comply with the requirements covering the category and the products are found to comply with UL's applicable requirements. The description and test result in this Report are only applicable to the samples investigated by UL and does not signify UL certification or that the product described is covered under UL's Follow-Up Service Program. When covered under UL's Follow-Up Service Program, the manufacturer is authorized to use the UL Classification Mark on such products which comply with UL's Follow-Up Service Procedure and any other application requirements of UL. The Classification Mark of UL on the product, or the UL symbol on the product and the Classification Mark on the smallest unit container in which the product is packaged, is the only method to identify products investigated by UL to published requirements and manufactured under UL's Classification and Follow-Up Service.

This Report is intended solely for the use of UL and the Applicant for establishment of UL certification coverage of the product under UL's Follow-Up Service. UL retains all rights, title and interest (including exclusive ownership) in this Report and all copyright therein. Unless expressly authorized in writing by UL, the Applicant shall not disclose or otherwise distribute the Report or its contents to any third party or use this Report for any purpose other than to establish UL certification and become eligible for Follow-Up Service for the product described in this Report. Any other use of the Report including without limitation, evaluation or certification by a party other than UL unless part of a certification scheme, is prohibited and renders the Report null and void. UL shall not incur any obligation or liability for any loss, expense, or punitive damages, arising out of or in connection with the use or reliance upon the contents of this Report to anyone other than the Applicant as provided in the agreement between UL and Applicant. Any use or reference to UL's name or certification mark by anyone other than the Applicant in accordance with the agreement is prohibited without the express written approval of UL or any authorized licensee of UL. Any information and documentation involving UL Mark services are provided on behalf of UL or any authorized licensee of UL. UL shall not otherwise be responsible to anyone for the use of or reliance upon the contents of this Report.

Test Record by:

Brian Foley
Engineer
Built Environment

Reviewed by:

Jamila Shawon
Staff Engineer
Built Environment