

**Dimensjon og vekt, ABS-rør LT-40 PN-10, gasser/ væsker densitet <math><1\text{kg/m}^3</math>**

Utv. dia. [mm]	Rørtykk. [mm]	Rørvekt [kg/m]	Rør + Vann [kg/m]	Klammeravst. 20 °C [m]	Klammeravst. 50°C [m]
20,0	1,50			0,90	0,60
25,0	1,80			1,00	0,70
32,0	2,00			1,10	0,80
40,0	2,50			1,20	0,90
50,0	3,20			1,30	1,00
63,0	4,00			1,40	1,10
75,0	4,70			1,50	1,20
90,0	5,70			1,60	1,20
110,0	6,90			1,80	1,30
125,0	7,90			1,80	1,30
140,0	8,80			2,00	1,50
160,0	10,00			2,10	1,70
200,0	12,50			2,20	1,80
225,0	14,1			2,30	1,80

**Densitet**

1,25 1,50 1,75 2,00

Ved loddrett montering av rør benyttes faktor 1,3

**Korreksjons-faktor**

0,90 0,83 0,77 0,70

**Dimensjon og vekt, PVC-rør PN-10, gasser/væsker densitet <math><1\text{kg/m}^3</math>**

Nom. dia. [DN]	Utv. dia. [mm]	Rørtykk. [mm]	Rørvekt [kg/m]	Rør + Vann [kg/m]	Klammeravst. 20 °C [m]	Klammeravst. 40°C [m]
10,0	16,0	1,20	0,08	0,23	0,80	0,50
15,0	20,0	1,50	0,13	0,35	0,90	0,90
20,0	25,0	1,90	0,20	0,55	0,95	0,65
25,0	32,0	2,40	0,33	0,91	1,05	0,70
32,0	40,0	3,00	0,51	1,42	1,05	0,70
40,0	50,0	3,70	0,79	2,21	1,40	1,10
50,0	63,0	4,70	1,26	3,51	1,50	1,20
65,0	75,0	5,60	1,78	4,98	1,65	1,35
80,0	90,0	6,70	2,56	7,17	1,80	1,50
100,0	110,0	8,20	3,83	10,71	2,00	1,70
125,0	140,0	10,40	6,18	17,34	2,25	1,95
150,0	160,0	11,90	8,08	22,65	2,40	2,10
	180,0	13,40	10,24	28,67		
	200,0	14,90	12,65	35,40		
	225,0	16,70	15,96	44,79		
	250,0	18,60	19,74	55,31		
	280,0	20,80	24,73	69,37		
	315,0	23,40	31,30	87,79		