

Technical Data Sheet

技术指标

Emulsion Chopped strand mat
乳剂短切毡

product specification 产品规格

M111E225、M111E250、M111E300、M111E375、M111E450、M111E600

Identification 规格说明



Example / 举例: M111E300

M: chopped strand mat /表示短切毡;

11: E-Glass /表示无碱玻璃;

1: standard chopping roving /常规短切纱生产;

P: Emulsion binder/乳剂粘结剂;

300: Nominal weight per square meter (g/m²)/单位面积质量 (g/m²);

Specification 技术参数

Specifications 技术参数		Test method 测试方法	Tolerance 偏差范围, %	Remark 备注
Area Weight 单位面积质量 (g/m ²)		ISO 3374	±10.0%	
Tensile Strength 拉伸强度 (N)	Vertical(纵向)	ISO 3342	≥40	
	Horizontal(横向)		≥40	
L.O.L 可燃物含量%		ISO 1887	2.0~8.0	
Moisture Content 含水率%		ISO 3344	≤0.20	

Packing 包装

Product is manufactured in form of a roll wound on a paper tube and then packed in a plastic film and placed within a cardboard carton. on pallet. 产品生产时卷于纸芯管上, 然后用塑料薄膜包装, 置于纸箱中, 采用托盘装。

Above package is standard one, any other package style is negotiable by both of us. 此包装为一般情况, 包装方式可由供需双方协商而定。

Storage 贮存

It is recommended that the fiber glass are stored in a cool and dry environment. Recommended temperature range of storage is between 10 ~ 30°C and relative humidity between 50 ~ 75%. The fiber glass should remain in the packaging until just prior to use.

推荐玻璃纤维产品存放在通风干燥的环境中。贮存温度范围建议为 10~30°C 之间, 相对湿度为 50~75%。产品在使用前, 需保持包装完好状态。

注 Remark: Other specification is available upon request 以上参数仅表明此系列产品的一般情况, 对于正式定单, 各参数以客户确认为准。