Minimalist Edition

Digital Color Card

SANTANA

C-3201

C-3202



C-3204



C-3205

C-3208

C-3209

C-3210



C-3212



C-3214

C-3216

INK FREE | **ANTI MICROBIAL** | **FIRE RETARDANT** | **PHTHALATE FREE** | **QUICK SHIP**

* Colors shown are indicative references only and will vary dependent on screen resolution

CSL LEATHER

www.csl-leather.com

HEAD OFFICE : **PT. BERKAT UNGGUL PRATAMA**
Komplek Citta Graha, Jl. Panjang No. 26 Blok 2L | Jakarta 11520 - Indonesia | +62 21 5819089

SHOWROOM : **LEDER HAUS**
JAKARTA • Komplek Cipete Square, Jl. Cipete Raya 55 No.7 | Jakarta 12410 - Indonesia | +62 21 75900 679
BANDUNG • Komplek Batununggal Indah, Jl. Batununggal Indah Raya No. 415 | Bandung 40266 - Indonesia | +62 22 8730 7759
BALI • Komplek Istana Kuta Galeria, Jl. Patih Jelantik, Blok PM1 No.6 | Kuta, Badung, Bali 80361 - Indonesia | +62361 4752 806

PATTERN ILLUSTRATION

APPLICATIONS

Dining Chair

Office Chair

Sofa

Santana

DESCRIPTION

Minute pebble grain leather and matte polish surface are the main characters of this collection. Thanks to its anti stain technology in protecting the surface from any pen marks or hard stains, the lively color palletes and aesthetic smooth grain will always vibrate throughout any designs. The perfect candidate for those who posses modern straight forward design styles and dare to be different among the crowd.

SPECIFICATIONS

Thickness	1.20 mm
Width	137 cm
Special Surface Finish	Smooth Grain
Composition	PVC & Woven Polyester
Usage	Indoor Upholstery
Repeat	No

PERFORMANCE

Abrasion	40.000 rubs
Flammability	FMVSS-302
Phthalate Free	REACH
Anti Microbial	AATCC-147

Abrasion	ASTM - D4966	40.000 rubs
Tensile Strength	ASTM - D751	Warp: 39 kg/3 cm, Weft: 19 kg/3 cm
Elongation	ASTM - D751	Warp: 87%, Weft: 239%
Tear Strength	ASTM - D4704	Warp: 5.02 kg/4 cm, Weft: 4.10 kg/4 cm
Adhesion Strength	ASTM - D751	Warp: 2.75 kg/3 cm, Weft: 3.45 kg/3 cm
Flexibility Strength	ASTM - D6182	20.000 cycles
Bursting Strength	ASTM - D3786	16 kg/cm²
Blocking Test	ASTM - D6116	Pass (No Blocking)
Color Fastness Test (Rubbing Test)	ASTM - D4157	Grade 4.5

** The above tests mentioned are guidelines for synthetic leather used in upholstery but do not necessarily indicate its lifespan. When used in different applications, factors such as the quality of craftsmanship, cleaning methods, proper placement, and handling will all impact its durability.*

LEATHER

www.csl-leather.com

HEAD OFFICE : PT. BERKAT UNGGUL PRATAMA
Komplek Citta Graha, Jl. Panjang No. 26 Blok 2L | Jakarta 11520 - Indonesia | +62 21 5819089

SHOWROOM : LEDER HAUS
JAKARTA • Komplek Cipete Square, Jl. Cipete Raya 55 No.7 | Jakarta 12410 - Indonesia | +62 21 75900 679
BANDUNG • Komplek Batununggal Indah, Jl. Batununggal Indah Raya No. 415 | Bandung 40266 - Indonesia | +62 22 8730 7759
BALI • Komplek Istana Kuta Galeria, Jl. Patih Jelantik, Blok PM1 No.6 | Kuta, Badung, Bali 80361 - Indonesia | +62361 4752 806

©2024 Leder Haus. All Rights Reserved.

LEDER HAUS®

THE LEATHER SPECIALIST

HOW TO CARE FOR SYNTHETIC LEATHER

☑ DO's

What you **SHOULD** do

- Use a soft, damp cloth to clean the surface of the material
- Rub the surface slowly with intense
- If it is stained with a fairly intense dye, try to clean the area with a damp cloth as soon as possible
- If there are stains that are still left behind, use a special cleaner for synthetic leather to help remove the stains

☒ DONT's

What you **SHOULDN'T** do

- Do not use rough/sharp materials (such as a brush) to clean the surface
- Do not use harsh (chemical) cleaning products such as: bleach, detergent, thinner, and others

Note:

Ink, permanent marker, denim and other strong textile dyes may be difficult or cannot to remove perfectly, especially on light colored synthetic leather

Test Report

Number : TWNC01344954

Date Issued : Mar 14, 2025

Applicant: PT BERKAT UNGGUL PRATAMA
KOMPLEK CITTA GRAHA
JL. PANJANG NO. 26 BLOK 2L, KEDOYA
SELATAN, KEBON JERUK, JAKARTA BARAT
ATTN: ENDANG MAWARNI S

Sample Description:

One (1) group of submitted samples said to be :

Sample Description	: CSL - SYNTHETIC LEATHER
Order/Style No.	: ALL STYLE
Buyers Company Name	: PT BERKAT UNGGUL PRATAMA
Country of Destination	: All Country
Country of Origin	: Taiwan
Testing Stage	: Production Sample
Date Sample Received	: Mar 04, 2025
Date Test Started	: Mar 04, 2025

Test Conducted:

As requested by the applicant, for details please refer to attached pages.

Authorized By:
On behalf of Intertek Testing Services Taiwan Limited

Anna Jing
Assistant General Manager

Signed by:

Thomas Chou
Manager

Intertek Testing Services Taiwan Ltd.
8F., No. 423, Ruiguang Rd., Neihu District, Taipei 114690, Taiwan, R.O.C.
全國公證檢驗股份有限公司
114690 台北市內湖區瑞光路 423 號 8 樓
Tel: (+886-2) 6602-2888 · 2797-8885 Fax: (+886-2) 6602-2405

Number : TWNC01344954

Test Conducted :

1. Antibacterial Activity Test

As per AATCC TM147-2011(2016)e

Test Organism	:	*Staphylococcus aureus* (ATCC 6538) *Klebsiella pneumoniae* (ATCC 4352)
Sterilization Of Sample Before Test	:	No Sterilization
Incubation Temperature	:	37±2℃
Incubation Period	:	18 - 24 Hours
Agar Medium	:	Nutrient Agar
Tested Sample Size	:	25×50mm

Result :

Test Organism	Test Side	Result
Staphylococcus aureus (ATCC 6538)	Green side	Inhibition of growth beneath the specimen only. (Without clear zone)
Klebsiella pneumoniae (ATCC 4352)	Green side	Inhibition of growth beneath the specimen only. (Without clear zone)

Remark : Clear zone = Clear area of no growth of a microorganism

As per applicant's provide Reference Rating	
Result	Anti-Bacterial Activity
Growth of test miroorganism was observed directly underneath the tested specimen	Not Acceptable
No growth of test miroorganism was observed directly underneath the tested specimen	Acceptable

Comment:

Staphylococcus aureus (ATCC 6538)	Acceptable
Klebsiella pneumoniae (ATCC 4352)	Acceptable

Intertek Testing Services Taiwan Ltd.
8F., No. 423, Ruiguang Rd., Neihu District, Taipei 114690, Taiwan, R.O.C.
全國公證檢驗股份有限公司
114690 台北市內湖區瑞光路 423 號 8 樓
Tel: (+886-2) 6602-2888 · 2797-8885 Fax: (+886-2) 6602-2405

Number : TWNC01344954

End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: http://www.intertek-twn.com/terms/. *Intertek's responsibility and liability are limited to the terms and conditions of the agreement.*

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.
Reporting Statements of Conformity: *Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.*

Intertek Testing Services Taiwan Ltd.
8F., No. 423, Ruiguang Rd., Neihu District, Taipei 114690, Taiwan, R.O.C.
全國公證檢驗股份有限公司
114690 台北市內湖區瑞光路 423 號 8 樓
Tel: (+886-2) 6602-2888 · 2797-8885 Fax: (+886-2) 6602-2405

Test Report

No.: HTH25300014 DATE: 2025/03/11

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

The following sample(s) was/were submitted and identified by/on behalf of the applicant as :

Sample Description	:	CSL-SYNTHETIC LEATHER
Style/Item No.	:	ALL STYLE
Sample Receiving Date	:	2025/03/05
Testing Period	:	2025/03/05 to 2025/03/11

Test Requested : The test was specified by client, please refer to the result table(s) for details.

Test Result(s) : Please refer to next page(s).

Singh Hsiao / Asst. Manager
Signed for and on behalf of
SGS TAIWAN LTD.
Chemical Laboratory - Taipei

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

Test Part Description

No.1 : Green synthetic leather with gray fabric backing

Test Result(s)

Test Item(s)	Method	Unit	RL	Result
				No.1
Dibutyl phthalate (DBP) (CAS No.84-74-2)	With reference to ISO 14389:2022. Analysis was performed by GC-MS.	mg/kg	30	n.d.
Butyl benzyl phthalate (BBP) (CAS No.85-68-7)		mg/kg	30	n.d.
Bis(2-ethylhexyl) phthalate (DEHP) (CAS No.117-81-7)		mg/kg	30	n.d.
Diisobutyl phthalate (DIBP) (CAS No.84-69-5)		mg/kg	30	n.d.
1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich (DIHP) (CAS No.71888-89-6)		mg/kg	30	n.d.
Diisopentyl phthalate (DIPP) (CAS No.605-50-5)		mg/kg	30	n.d.
Di-n-hexyl phthalate (DNHP) (CAS No.84-75-3)		mg/kg	30	n.d.
Bis(2-methoxyethyl) phthalate (DMEP) (CAS No.117-82-8)		mg/kg	30	n.d.
Di-n-pentyl phthalate (DNPP) (CAS No.131-18-0)	Method: With reference to ISO 14389 method. Analysis was performed by GC/MS.	mg/kg	30	n.d.

Note:

1. mg/kg = ppm ; 0.1% = 1000 ppm
2. RL = Reporting Limit
3. n.d. = Not Detected = Less than RL
4. The testing item(s) was/were subcontracted to SGS Taiwan Ltd. Chemical Laboratory – Kaohsiung.
5. The report is invalid if it is partly reproduced or used.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

*** The tested sample / part is marked by an arrow if it's shown on the photo. ***

HTH25300014

Appearance of the sample-Front view

HTH25300014

Appearance of the sample-Back view

**** End of Report ****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

intertek
Total Quality. Assured.

ORIGINAL

Report Number: JKTH23001290

Test Report

Applicant : PT Berkat Unggul Pratama
Komplek Citta Graha Jl Panjang No 26
Blok 2L Kedoya Selatan Kebon Jeruk
Jakarta Barat

Attn : Endang

Date : May 11, 2023

Sample description:

One (1) group of submitted sample said to be :

Material Name	:	**CSL**
Country of Original	:	Taiwan
Buyers Company Name	:	PT Berkat Unggul Pratama
Date sample received	:	Apr 18, 2023
Testing period	:	Apr 18, 2023 to May 11, 2023

****

Test conducted:

As requested by the applicant, for details please refer to attached pages.

****

Conclusion:

Section No.	Test Name	Evaluation
230428004-MT-1-EN.001	Flammability	Conforming

****

Remark:

Test subcontracted to Intertek China

FN

Prepared and checked by:
For Intertek Indonesia

Made Widyani
Operation Manager - Testing

This report shall not be reproduced wholly or in parts without written approval of the laboratory

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Term and Conditions.
For the complete term and condition, please visit : http://www.intertek.com/terms/

PT. Intertek Utama Services Citrabuana Indoloka Building
Jl. Cikini IV No.2, Gondangdia
Jakarta 10330, Indonesia

Telp. (62-21) 391 8584 (Hunting), 391 8574 (Direct), Fax. (62-21) 391 8345
Hardline Laboratory:Jakarta (62-21) 391 6611, Semarang (62-24) 762 7107 / 762 7325
Email : hlcoordinator.indonesia@intertek.com **Website:** www.intertek.com

Test Report **Report Number: JKTH23001290**

TEST ITEMS, METHOD AND RESULTS:

230428004-MT-1-EN.001	**Flammability**
Ref. Specs Section	FMVSS 302-2021
Date Tested	2023-05-06~2023-05-07
Sample No.	IAS2304280040101-1~IAS2304280040101-5
Test Method	Sample Preparation Methods: specimens made by customer; Sample Handing: Temperature 21℃ ; Relative humidity50% ; Time 24h ; Test environment: Temperature 23±2℃ ; Relative humidity50±5% . The test was performed in accordance with FMVSS 302-2021. Specimens size 356×100×1.2mm,No wires Gas flame height: 38mm. Duration for exposure to the flame: 15s.
Acceptance Criteria	≤102mm/min
Deviation	None

Test Results

Sample ID	Burn Length (mm)	Burn Time (s)	Burn Rate (mm/min)
IAS2304280040101-1	/	/	0
IAS2304280040101-2	/	/	0
IAS2304280040101-3	/	/	0
IAS2304280040101-4	/	/	0
IAS2304280040101-5	/	/	0
Burning rate max	0		

Evaluation Conforming

Test Instruments

Equipment No.	Equipment Name	Calibration Due Date
MENV501	Flammability Chamber	N/A
MENV672	Steel ruler	2023-12-26
MENV896	Electronic stopwatch	2023-05-26
MENV758	Thermocouple thermometer	2023-09-26
MENV753	Anemometer	2023-07-31

Observations & Remarks

None

Pictures

This report shall not be reproduced wholly or in parts without written approval of the laboratory

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Term and Conditions.
For the complete term and condition, please visit : http://www.intertek.com/terms/

PT. Intertek Utama Services Citrabuana Indoloka Building Jl. Cikini IV No.2, Gondangdia Jakarta 10330, Indonesia
Telp. (62-21) 391 8584 (Hunting), 391 8574 (Direct), Fax. (62-21) 391 8345
Hardline Laboratory:Jakarta (62-21) 391 6611, Semarang (62-24) 762 7107 / 762 7325
Email : hlcoordinator.indonesia@intertek.com **Website:** www.intertek.com

Before Test

After Test

****

END OF THE TEST REPORT

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for whichit is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at http://www.intertek.com/terms

This report shall not be reproduced wholly or in parts without written approval of the laboratory

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Term and Conditions.
For the complete term and condition, please visit : http://www.intertek.com/terms/

PT. Intertek Utama Services Citrabuana Indoloka Building Jl. Cikini IV No.2, Gondangdia Jakarta 10330, Indonesia
Telp. (62-21) 391 8584 (Hunting), 391 8574 (Direct), Fax. (62-21) 391 8345
Hardline Laboratory:Jakarta (62-21) 391 6611, Semarang (62-24) 762 7107 / 762 7325
Email : hlcoordinator.indonesia@intertek.com Website: www.intertek.com

Hardline Laboratory

TEST REPORT

Report No.： HU30003/2025
Page： 1 of 2
Date： MAR. 12, 2025

PT BERKAT UNGGUL PRATAMA
KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

The following merchandise was submitted and identified by the applicant as:

Product Description: CSL-SYNTHETIC LEATHER
Style/Item No.: ALL STYLE

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested: For compliance with Federal Motor Vehicle Safety Standard No.302 Flammability of interior materials(49 CFR 571.302).

Test Result: ---See following sheet(s)---

Date of Receipt: Mar. 04, 2025

Testing Period: Mar. 04, 2025 ~ Mar. 12, 2025

Signed for and on behalf of SGS Taiwan Ltd.

Lawrence Yang
Asst. Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Test Result:

For compliance with Federal Motor Vehicles Safety Standard No.302 Pass

Flammability of interior materials

	Filling			Warp		
	Char Length (mm)	After Flame (sec.)	Burn Rate (mm/min)	Char Length (mm)	After Flame (sec.)	Burn Rate (mm/min)
1.	0	0	SE	0	0	SE
2.	0	0	SE	0	0	SE
3.	0	0	SE	0	0	SE

Note: SE = Self - Extinguish. The material ignites but extinguishes itself before reaching the 38 mm point from the clamped start of the specimen.

Test Requirement: The burn rate shall not exceed 102 mm per minute.

Conclusion: The submitted sample(s) **complies with** the requirements of Federal Motor Vehicle Safety Standard No. 302 Flammability of interior materials (49 CFR 571.302).

Remark:

1. The content of this report is invalid if it is not presented as the entire report.
2. The decision rule of the statements of conformity is following the ILAC G8:09/2019 by using the simple acceptance decision rule.

– Picture(s) –

Photo A: Appearance of the sample(s)

--- End of Report ---

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.