







Slot Car Corner - Adhesives Chart - CA (cyanoacrylate)				
	IC2000	INSTA-FLEX+	INSTA-CURE	MAXI-CURE
				
Quantity	1/2 oz.	1/2 oz.	1 oz.	1 oz.
Cure Time	10-15 seconds (urethane) 15-20 seconds (silicone)	5-10 seconds (urethane) 10-15 seconds (silicone)	3 seconds	10-25 seconds
Color	Dark	Clear	Clear	Clear
Viscosity	Medium	Medium	Thin	Thick
Flexibility	Medium	High	Low	Low
Main Application	Gluing tires to wheels	Gluing tires to wheels	Securing bronze bushings to chassis	Securing front axle blocks to chassis
Notes	When cured, is pliable enough to be carved with a hobby knife. Once a tire is glued to a wheel with IC2000, the bond is permanent.	Best choice when esthetics and a flexible bond are important. Once a tire is glued to a wheel with INSTA-FLEX+, the bond is permanent.	Wicks deep into joints by capillary action and cures in a matter of a few seconds. When CA's cure, they give off a vapor that can irritate the nose and eyes.	Can be carved with a knife or razor blade and sanded and feathered to form a finish indistinguishable from plastic. Avoid contact with clear plastic such as windshields.