

# **Customer Specification** #59-801 Cane Mesh Sleeves

# **PRODUCT NOMENCLATURE**

Manufacturing Code: Manufacturing Name: Marketing Glove ASPN Code(s): 59-800 & 59-801 **Cane Mesh Sleeves** 

See Below ("Styles/Dimensions Within Series")

### PRODUCT DESCRIPTION

Weight: Color:

٠

11 oz./sq.yd. (+ 15%) Black

Composition: Thickness: Packaging:

**100% Starched Polyester** .053" 96 Dozens/Case

# **OUTSTANDING CHARACTERISTICS & APPLICATIONS**

Superior flexibility

Product Classification:

Excellent resistance to punctures, snags and abrasions

Sleeve

- Offers good cut resistance
- **APPLICATIONS:** Food processing, Meat packing, Assembly, Electronics, General manufacturing

#### **PERFORMANCE CHARACTERISTICS**

- Cut Resistance (CPPT)
- Cut Resistance (TDM-100) Instron Ball Burst

1490 grams (average) 1865 grams (average) 475 psi minimum

ASTM F 1790, ANSI Level 3 ASTM F2992, ANSI Level A4 ASTM D 3787

STYLES/DIMENSIONS WITHIN SERIES			
STYLE	ASPN CODE	DIMENSIONS/COLOR	
59-801 (CMS-7B)	950261	7" Women's (Black)	
59-801 (CMS-8B)	950262	8" Men's (Black)	
59-801 (CMS-9B)	950263	9" Men's (Black)	

#### **GUARANTEE**

These products are manufactured to rigid specifications under strict conditions of process and quality control set forth by Ansell. They are guaranteed against defect in workmanship or material and will be replaced or credited if returned for examination. This guarantee does not apply to deterioration caused by abuse, excessive wear or age.

#### **GENERAL INFORMATION**

Three (3) years in cool, covered conditions. Extended exposure to direct sunlight or SHELF LIFE: excessive heat may reduce shelf life.

<b>Originator</b> :	Paul McMorrow	Date: 10/05/01	Revision #:
	Paul McMorrow	09/20/05	1 (added weight/thickness data)
	Paul McMorrow	10/02/06	2 (deleted non-applicable latex warning statement)
	Paul McMorrow	06/24/10	<b>3</b> (added ANSI performance level for cut resistance)
	Paul McMorrow	03/20/13	<b>4</b> (deleted obsolete style 59-800 white)
	Paul McMorrow	11/31/18	5 (added TDM-100 Cut data)

NEITHER THIS NOR ANY STATEMENT MADE BY OR ON BEHALF OF ANSELL HEREIN IS A WARRANTY THAT ANY PRODUCT IS FIT FOR A PARTICULAR PURPOSE AND ANSELL SHALL NOT BE LIABLE TO ANYONE WITH RESPECT TO THIS INFORMATION.

This document is the property of Ansell and the information contained herein is proprietary to Ansell.