



### MRO INDUSTRIAL ENAMEL

A superior industrial spray paint formulated for maintenance operations where maximum performance is required. This high solids paint does not run or sag, and gives twice the coverage of conventional spray paints. Can be applied to bare metal, but for maximum protection, use our MRO Red Iron Oxide Primer (663-104) or Light Gray Primer (663-103). Resists oil, gas, heat, and sunlight.

#### Suggested Uses:

- Wood
- Home
- Marine
- Metal
- Industrial
- Construction

#### Packaging:

Cans per case:	6
Shipping weight per case:	9 lbs.
Container:	20 fluid ounce can
Label weight:	16 ounces (454 grams)
Shipping Classification:	Limited quantity, UN 1950
Hazard Class:	2.1

#### Properties:

Coverage:	Up to 18 square feet
Cleanup:	Paint or lacquer thinner
Flash Point:	4°F
Specific Gravity:	0.82
Solids Content:	Glosses: 33% Flats: 35% Metallics: 23%
MIR Value:	Glosses: 0.85, cannot exceed 0.95 Flats: 0.74, cannot exceed 0.80 Metallics: 1.13, cannot exceed 1.25
HAPs Content:	Glosses: 13% Flats: 11% Metallics: 37%
Storage Temperature:	40°-100°F
Application Temperature:	50°-90°F
Gasoline Resistance:	Yes
Heat Resistance:	300°F
Resin System:	Chain Stopped alkyd
Shelf Life:	Guaranteed for 2 years
Food Contact Rating:	Category 21: Acceptable

#### Dry Time\*:

To Touch:	30 minutes
To Recoat:	Before 1 hour, or after 48 hours
Hard Cure:	2-3 days

\*At 72F, 50% humidity, 1.5 mil thickness

\*\*Curing/Recoat time is extended with multiple coats and excessively thick coats\*\*

#### Gloss\*:

High Gloss: >80  
Flat: <15

\*as measured on a 60-degree gloss meter

#### Available Colors:

<u>Part Number:</u>	<u>Description:</u>
663-101	Gloss White
663-125	Cardinal Almond

Distributed by:  
Tacoma Screw Products, Inc.  
2001 Center Street  
Tacoma, WA 98409