CLOSED-CELL FOAM PIPE INSULATION

>> 663 SERIES

SPECIFICATION

Sioux Chief 663 Series pipe/tube insulation shall be used in plumbing and HVAC systems to reduce condensation and heat loss in hot or cold water distribution lines. Insulation shall be made from non-porous, closedcell polyethylene foam, manufactured without CFCs, HCFCs, HFCs, PBDEs, or formaldehyde. Insulation shall have very low water vapor permeability, superior flexibility, and excellent microbial and fungi resistance.

MATERIALS

Closed-cell, polyethylene foam - black color

INSTALLATION NOTES

Material is inert and product is approved for use with all types of water distribution piping. Insulation must be properly sized to perform as expected. Do not stretch the product during installation - tubes should be pushed into place rather than pulled. Systems should be unheated at time of installation. All joints and seams should be sealed for proper performance.

TENSILE STRENGTH

25/50 (ASTM E84)

FLAME/SMOKE RATING

30 PSI

TEMPERATURE RATING

Working: -200°F min | 200°F max

ELONGATION 50%

THERMAL CONDUCTIVITY/STABILITY

75°F mean temp: 0.27 | 120°F mean temp: 0.295 Linear shrinkage: Less than 3% @ 200°F

R-VALUES

	3/8" Wall	1/2" Wall	3/4" Wall	1" Wall
5/8" ID	2.57	3.54	5.70	8.07
7/8'' ID	2.28	3.15	5.07	7.20
1-1/8" ID	2.17	2.98	4.88	6.72
1-3/8" ID	2.11	2.88	4.88	6.41
1-5/8" ID	2.22	2.97	4.56	6.36
2-1/8" ID	2.02	2.71	4.03	5.83
2-3/8" ID	n/a	2.71	4.20	5.74
2-5/8" ID	2.05	2.71	4.16	5.68
3-1/2" ID	n/a	2.74	n/a	n/a

ITEM # SUBMITTED			
JOB NAME			
LOCATION			
ENGINEER			
CONTRACTOR			
PO# T/	AG		





Create Item Number

663-<u>ABC</u>

e.g. 663-07838HS: Foam pipe insulation - 7/8" ID x 3/8" wall with Half-slit seam - Box

INNER DIAMETER A WALL THICKNESS B SEAM TYPE B **058** = 5/8" ID 078 = 7/8" ID 118 = 1-1/8" ID **38** = 3/8" Wall HS = Half-slit seam 138 = 1-3/8" ID 158 = 1-5/8" ID **218** = 2-1/8" ID 12 = 1/2" Wall SS = Self-seal seam 238 = 2-3/8" ID 258 = 2-5/8" ID **312** = 3-1/2" ID **34** = 3/4" Wall 10 = 1" Wall

Note: Not all option combinations are available - See website for full product listing



Sioux Chief Manufacturing Company | P: 1.800.821.3944 | F: 1.800.758.5950 | www.siouxchief.com

